

List of chemical resistance of materials in contact with liquid

ANALYSETTE 22 NeXT & ANALYSETTE 28 ImageSizer

LASER PARTICLE SIZER & PARTICLE SIZER

This chart information is based on FRITSCH's knowledge and experience and are intended as a guide and not as a guarantee. We cannot assure the perfect performance of the materials as that depends on many factors as working pressure, pressure picks, fluid, ambient temperature, fluid temperature, concentration, duration of exposure, etc...





Fritsch GmbH
Milling and Sizing
Industriestrasse 8
D - 55743 Idar-Oberstein
Telephone: +49 (0) 6784/ 70-0
Email: info@fritsch.de
Internet: www.fritsch.de

Table of contents

1	Materials in contact with liquid.....	4
2	Abbreviations.....	5
3	List of chemical resistance.....	7
3.1	KEY.....	7
3.2	Note.....	7
3.3	Table 1.....	7
3.4	Table 2.....	97
3.5	Table 3.....	105

Materials in contact with liquid

1 Materials in contact with liquid

Wet dispersion units	Materials used in the sample circuit:
Wet dispersion unit (22.9200.00 & 28.2500.00)	stainless steel ¹ , PTFE (Teflon) ² , N-BK7 glass, Viton ^{®2} , Viton [®] Extreme ³ , POM ^a , Brass, Silicone hoses (LEZ-SIL 60 PFT) ^o
"Conversion Kit Extended" for extreme chemical resistance (22.9287.00 & 22.9288.00)	FFKM (Kalrez ^{®3}): replaces Viton ^{®2} & Viton [®] Extreme ³ ; TPE (LEZ-SAN Santoprene ^{®3}): replaces Silicone hoses (LEZ-SIL 60 PFT)

¹ See Table 1 and Table 2

² See Table 2

³ See Table 1

^o See Table 2 (Silicone (peroxide/ platinum- cured))

^a See Table 3

2 Abbreviations

ASTM D1418 Abbreviation	Chemical name	Trade names	PPE Prefix
ACM	Polyacrylate (Polyacrylic)	Europrene-AR [®] , Krynac [®] , Nipolar [®] , Hycar [®] , Cyanacryl [®] , Noxtite-PA [®]	P
AEM	Ethylene Acrylic	Vamac [®] W	W
AQU / EU	Polyester Urethane Polyether Urethane	Vibrathane [®] , Pellethane [®] , Urepan [®] , Elastothane [®] , Adiprene [®] , Desmopan [®] , Vulkollan [®] , Estane [®]	Q
CR	Chloroprene	Neoprene [®] , Skyprene [®] , Butclor [®] , Baypren [®] , Denka [®]	C
CSM	Chlorosulphonylpolyethylene (Chlorosulphonated polyethylene)	Hypalon [®] , Noralon [®]	L
ECO	Epichlorohydrin	Hydrin [®] , Herclor [®] , Gechron [®]	H
EPD / EPDM	Ethylene-Propylene Copolymer, Ethylene-Propylene Terpolymer	Buna-AP [®] , Dutral [®] , Epsyn [®] , Nordel [®] , Epcar [®] , Keltan [®] , Royalene [®] , Polysar-EDM [®]	E
FEP / PFA	Fluoroethylene Propylene, Perfluoroalkoxy	Teflon FEP [®] , Neoflon FEP [®] , Teflon PFA [®] , Neoflon PFA [®]	D
FEPM	See TFE/P	Aflas [®] , Dyneon BRE [®] ; Viton Extreme [®]	A
FFKM/FFPM*	Perfluoroelastomer	Perlast [®] , Kalrez [®] , Chemraz [®]	G
FKM/FPM*	Fluoroelastomer	Viton [®] , Dai-el [®] , Fluorel [®] , Tecnoflon [®]	V
FVMQ	Fluorosilicone	Silastic, LS [®] , FSE [®]	F
NBR / XNBR	Nitrile Butadine, Carboxylated Nitrile	Breon, Butakon [®] , Chemigum [®] , Hycar [®] , Buna-N [®] , Butacril [®] , Paracil [®] , Perbunan [®] , Krynac [®] , Europrene-N [®] , Nipol [®]	N
HNBR	Hydrogenated Nitrile	Therban [®] , Tornac [®] , Zetpol [®]	Z
IIR	Butyl Rubber	Exxon Butyl [®] , Polysar Butyl [®] , Esso Butyl [®]	J
IR	Isoprene	Shell Isoprene Rubber [®]	R
NR	Natural Rubber	Natsyn [®]	R
POM	Polyoxymethylene		

Abbreviations

ASTM D1418 Abbreviation	Chemical name	Trade names	PPE Prefix
SBR	Styrene Butadine (Buna-S)	Cariflex S [®] , Plioflex [®] , Euro-prene [®] , Pliolite [®] , Buna Huls [®] , Carom [®] , Solprene [®]	B
TFE/P	Tetrafluoroethylene/Propylene	Aflas [®] , Flourel II [®] , Fluoraz [®]	A
TPE	Thermoplastisches Elastomer	LEZ-SAN Santoprene [®]	
VMQ / PVMQ	Silicone	Silastic [®] , Siloprene [®] , Rhodorsil [®] , Silplus [®]	S

3 List of chemical resistance

3.1 KEY

A - No effect; little noticeable change

B - Minor effect; slight corrosion or discoloration

C - Moderate effect; not recommended for continuous use; softening, loss of strength, swelling and/or shrinkage

D - Severe effect; not recommended for use; severe softening, swelling and/or shrinkage

3.2 Note

The CHEMICAL PROPERTIES of N-BK7 glass see: https://www.schott.com/d/advanced_optics/c36214d9-13c4-468c-bf40-8d438b89f532/1.30/schott-optical-glass-pocket-catalog-jan-2020-row.pdf

3.3 Table 1

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Abietic Acid		A	A		
Acetaldehyde	D	A	A	D	A
Acetamide	C	C	A	A	A
Acetanilide	C	A			
Acetic Acid, 30%		A	A	A	A
Acetic Acid, 5%	A	A	A	A	A
Acetic Acid, Glacial	B	A	A	A	A
Acetic Acid, Hot, High Pressure	D	B	A		A
Acetic Anhydride	D	C	A	A	A
Acetoacetic Acid	C	C	A		A
Acetone	D	B	A	A	A
Acetone Cyanohydrin	C	B	A	A	

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Acetonitrile	A	B	A	A	C
Acetophenetidine	A		A		
Acetophenone	D	C	A	B	
Acetotoluidide	A		A		
Acetyl Acetone	D	A	A	A	
Acetyl Bromide	A		A	D	
Acetyl Chloride	A	A	A	D	A
Acetylene	A	A	A	A	A
Acetylene Tetra-bromide	A	A	A		
Acetylene Tetra-chloride	A	A	A	D	
Acetylsalicylic Acid	A	A	A		
Acids, Non-organic		A	A		
Acids, Organic		A	A		
Aconitic Acid			A		
Acridine			A		
Acrolein	C	C	A	A	
Acrylic Acid	A	B		A	
Acrylonitrile	C	C	B	D	
Adipic Acid		A	B	B	
Aero Lubriplate	A	A	A		
Aero Shell 17 Grease	A	A	A		
Aero Shell 750	A	A	A		
Aero Shell 7A Grease	A	A	A		
Aero Shell IAC	A	A	A		
Aerosafe 2300	D	C	B		
Aerosafe 2300W	D	C	B		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Aerozene 50 (50% Hydrazine 50% UDMH)	D	C	B		
Air, Below 200°F	A	A	A		
Air, 200 - 300°F	A		A	D	
Air, 300 - 400°F	A		A		
Air, 400 - 500°F	C		B		
Aliphatic Dicarboxylic Acid	A		A	D	
Alkanes (Paraffin Hydrocarbons)	A	A	A		
Alkanesulfonic Acid	A		A		
Alkazene	B	A	A		
Alkenes (Olefin Hydrocarbons)	A	A	A		
Alkyl Acetone	C	C	A		
Alkyl Alcohol	A	A	A		
Alkyl Amine	A	B	B		
Alkyl Aryl Sulfo-nates	A		A		
Alkyl Aryl Sul-fonics	A		A		
Alkyl Benzene	A	A	A		
Alkyl Chloride	A	A	A		
Alkyl Sulfide*	A		A		
Alkylnaphthalene Sulfonic Acid	A		A		
Allyl Chloride	A		A	C	
Allylidene Diace-tate	C		B		
Alpha Picoline	C		A		
Aluminum Ace-tate	D	C	A	A	

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Aluminum Bromide	A	A	A	A	
Aluminum Chlorate	C	A	A	A	
Aluminum Chloride	A	A	A	A	B
Aluminum Ethylate			A	A	
Aluminum Fluoride	A		A	A	C
Aluminum Fluorosilicate*			A	A	
Aluminum Formate	C	C	A	A	
Aluminum Hydroxide	B	A	A	A	B
Aluminum Linoleate	A		A	A	
Aluminum Nitrate	A	A	A	A	A
Aluminum Oxalate	C		A		
Aluminum Phosphate	A	A	A		
Aluminum Potassium Sulfate	C	A	A		B
Aluminum Salts	A	A	A	A	
Aluminum Sodium Sulfate	C	A	A		
Aluminum Sulfate	A	A	A	A	B
Alums-NH3 -Cr -K	D	A	A		
Ambrex 33 (Mobil)	A	A	A		
Ambrex 830 (Mobil)	A	A	A		
Amines-Mixed	D	C	A	C	A
Aminoanthraquinone			A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Aminoazobenzene			A	A	
Aminobenzene Sulfonic Acid			A		
Aminobenzoic Acid			A		
Aminopyridine			A		
Aminosalicylic Acid			A		
Ammonia (Anhydrous)	D	B	A		A
Ammonia and Lithium Metal in Solution	D				
Ammonia, Gas, Cold	D		A		
Ammonia, Gas, Hot	D		A		
Ammonia, Liquid (Anhydrous)	D				A
Ammonium Acetate	C	C	A	A	
Ammonium Arsenate	C		A		
Ammonium Benzoate	C		A		
Ammonium Bicarbonate	C	C	A		
Ammonium Bisulfite	C		A		
Ammonium Bromide	A		A		
Ammonium Carbamate	C		A		
Ammonium Carbonate	A		A	A	A
Ammonium Chloride, 2N	A	A	A	A	C

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Ammonium Citrate	C		A		
Ammonium Dichromate	C		A		
Ammonium Diphosphate	C	A	A		
Ammonium Fluoride	A	A	B		
Ammonium Fluorosilicate*			A		
Ammonium Formate	C		A		
Ammonium Hydroxide, 3 Molar	C	A	B	A	A
Ammonium Hydroxide, Concentrated	D	A	B	A	A
Ammonium Iodide	A		A		
Ammonium Lactate	C		A		
Ammonium Metaphosphate	C		A		
Ammonium Molybdenate*	C		A		
Ammonium Nitrate, 2N		A	A	A	A
Ammonium Nitrite		A	A		A
Ammonium Oxalate	C		A		A
Ammonium Perchlorate	C		A		
Ammonium Perchloride			A		
Ammonium Persulfate 10%		A	A	A	A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Ammonium Per-sulfate Solution		A	A		
Ammonium Phosphate	D	A	A		
Ammonium Phosphate, Dibasic		A	A		A
Ammonium Phosphate, Mono-Basic		A	A		A
Ammonium Phosphate, Tri-basic		A	A		A
Ammonium Phosphite	C		A		
Ammonium Picrate	C		A		
Ammonium Polysulfide	C		A		
Ammonium Salicylate	C		A		
Ammonium Salts	C	B	A	A	
Ammonium Sulfamate	C	C	A		
Ammonium Sulfate	D	A	A	A	B
Ammonium Sulfate Nitrate	D		A		
Ammonium Sulfide	D	A	A		
Ammonium Sulfite	C	A	A	A	
Ammonium Thiocyanate	C	A	A		
Ammonium Thioglycolate	C		A		
Ammonium Thiosulfate	C	A	A	A	A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Ammonium Tungstate	C		A		
Ammonium Valerate	C		A		
Amyl Acetate	D	B	A	D	A
Amyl Alcohol	B	A	A	A	A
Amyl Borate	A	A	A		
Amyl Butyrate	A	A	A		
Amyl Chloride	A	A	A	D	B
Amyl Chloronaphthalene	A	A	A		
Amyl Cinnamic Aldehyde	A	C	A		
Amyl Laurate	A	A	A		
Amyl Mercaptan	A	A	A		
Amyl Naphthalene	A	A	A		
Amyl Nitrate	C		A		
Amyl Phenol		A	A		
Amyl Propionate	A	A	A		
Anderol, L- 826 (di-ester)	A	A	A		
Anderol, L- 829 (di-ester)	A	A	A		
Anderol, L-774 (di-ester)	A	A	A		
ANG-25 (Di-ester Base) (TG749)	A	A			
ANG-25 (Glyceral Ester)	A	A			
Aniline	C	A	A	A	A
Aniline Dyes	B	A	A	A	
Aniline Hydrochloride	B	A	A		
Aniline Oil	C	B	A	B	

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Aniline Sulfate	C		A		
Aniline Sulfite	C		A		
Animal Fats	A	A	A	B	
Animal Oil (Lard Oil)	A	A	A		
Anisole		A	A		
Anisoyl Chloride			A		
AN-O-3 Grade M	A				
AN-O-366	A				
AN-O-6	A				
Ansul Ether 161 or 181	D	C	A		
Anthracene	A	A	A		
Anthranilic Acid		A	A		
Anthraquinone		A	A		
Anti-freeze Solutions	C	A	A		
Antimony Chloride	A	A	A		
Antimony Pentachloride	A	A	A	A	
Antimony Pentafluoride		A	B		
Antimony Sulfate			A		
Antimony Tribromide	A		A		
Antimony Trichloride	A		A		D
Antimony Trifluoride	A		B		
Antimony Trioxide	A		A		
AN-VV-O-366b Hydr. Fluid	A	A	A		
Aqua Regia	B	A	A	D	D

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Arachidic Acid		A	A		
Argon	A	A	A	A	
Aroclor, 1248	A	A	A		
Aroclor, 1254	A	A	A		
Aroclor, 1260	A	A	A		
Aromatic Fuel -50%	A	A	A		
Arsenic Acid	A	A	A	A	A
Arsenic Oxide			A		
Arsenic Tri-chloride	D	C	A		
Arsenic Trioxide	D		A		
Arsenic Trisulfide	D		A		
Arsenites			A		
Arsine			A		
Aryl Orthosilicate			A		
Ascorbic Acid	C	A	A		
Askarel Transformer Oil	A	A	A		
Aspartic Acid	C	B	A		
Asphalt	A	A	A		A
ASTM Oil, No. 1	A	A	A	C	
ASTM Oil, No. 2	A	A	A	D	
ASTM Oil, No. 3	A	A	A	D	
ASTM Oil, No. 4	A	A	A	D	
ASTM Oil, No. 5	A	A	A		
ASTM Reference Fuel A	A	A	A	C	
ASTM Reference Fuel B	A	A	A	B	
ASTM Reference Fuel C	A	A	A	B	

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
ASTM Reference Fuel D	A	A	A		
ATL-857	A	A			
Atlantic Dominion F	A	A			
Atlantic Utro Gear-e	A	A			
Atlantic Utro Gear-EP Lube	A	A			
Aure 903R (Mobil)	A	A	A		
AUREX 256		A	A		
Automatic Transmission Fluid	A	A	A	D	
Automotive Brake Fluid	D	B	A		
AXAREL 9100					
Azobenzene			A		
Bardol B	A	A	A		
Barium Carbonate	C	A	A	A	A
Barium Chlorate	C	A	A		
Barium Chloride	A	A	A	A	A
Barium Cyanide	A	A	A		A
Barium Hydroxide	A	A	A	A	A
Barium Iodide	A	A	A		
Barium Nitrate	C	A	A		A
Barium Oxide	A	A	A		
Barium Peroxide	C	B	A		
Barium Polysulfide	C	B	A		
Barium Salts	A	A	A		
Barium Sulfate	A	A	A		A
Barium Sulfide	A	A	A	A	

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Bayol 35	A	A	A		
Bayol D	A	A	A		
Beer	A	A	A	A	
Beet Sugar Liquids	A	A	A	A	A
Beet Sugar Liquors	A	A	A	A	
Benzaldehyde	D	C	B	B	A
Benzaldehyde Disulfonic Acid			B		
Benzamide	A	A	A		
Benzanthrone	A	A	A		
Benzene	A	A	A	D	A
Benzene Hexachloride		A	A		
Benzenesulfonic Acid 10%	A	A	B		
Benzidine	A	A	A		
Benzidine 3 Sulfonic Acid	A	A	A		
Benzil	A	A	A		
Benzilic Acid	A	A	A		
Benzine (Ligroin)	A	A	A	D	
Benzocatechol	A	A			
Benzochloride	A	A	A		
Benzoic Acid	A	A	A	B	A
Benzoin	A	A	A	D	
Benzonitrile	C	B	A		
Benzophenone	A	A	A		
Benzoquinone	A	A	A		
Benzotrichloride	A	A	A		
Benzotrifluoride	A	A	A		
Benzoyl Chloride	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Benzoyl Peroxide			A		
Benzoylsulfonilic Acid	A	A	A		
Benzyl Acetate	C	C	A		
Benzyl Alcohol	A	A	A		
Benzyl Amine		C	B		
Benzyl Benzoate	A	A	A		
Benzyl Bromide	A		A		
Benzyl Butyl Phthalate	C	A	A		
Benzyl Chloride	A	A	A		
Benzyl Phenol	A	A	A	D	
Benzyl Salicylate	A		A		
Beryllium Chloride	A		A		
Beryllium Fluoride	A		A		
Beryllium Oxide	A		A		
Beryllium Sulfate	C		A		
Bismuth Carbonate	C	A	A		
Bismuth Nitrate	C		A		
Bismuth Oxide	C		A		
Bittern			A		
Black Liquor	A	A	A		
Black Point 77	A	A			
Blast Furnace Gas	A	A	A		
Bleach Liquor	A	A	A		
Bleach Solutions	A		B		
Borax	A		A		A
Borax Solutions	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Bordeaux Mixture	A	A	A		
Boric Acid	A	A	A	A	A
Boric Oxide	C		A		
Borneol	A	A	A		
Bornyl Acetate	A	B	A		
Bornyl Chloride	A		A		
Bornyl Formate	A		A		
Boron Fluids (HEF)	A	A	A		
Boron Hydride			A		
Boron Phosphate			A		
Boron Tribromide			A		
Boron Trichloride			B		
Boron Trifluoride			B		
Boron Trioxide			A		
Brake Fluid DOT3 (Glycol Type)	D	A	A		
Bray GG-130	A				
Brayco 719-R (VV-H-910)	D	A			
Brayco 885 (MIL-L-6085A)	A	A			
Brayco 910	D	B			
Bret 710	D				
Brine	A	A	A		
Brine (Seawater)	A				
Brom - 113					
Brom - 114	B				
Bromic Acid	C		A		
Bromine	A	A	A		D
Bromine Pentafluoride Factory	D	C	B		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Bromine Tri-fluoride Factory	D	C	B		
Bromine Water	A		B		
Bromobenzene	A	A	A		
Bromobenzene Cyanide	C		A		
Bromochlorotri-fluoroethane (Halothane)	A	A	A		
Bromoform	A		A		
Bromomethane (Methyl Bromide)	A	A	A		
Bromotrifluoro-ethylene (BFE)		A			
Bromotrifluoro-methane (F-13B1)		B	B		
Brucine Sulfate	C		A		
Buffered Oxide Etchants					
Bunker Oil	A	A	A		
Bunker's "C" (Fuel Oil)	A	A	A		
Butadiene (Mon-omer)	A	A	A		A
Butane	A	A	A	A	A
Butane, 2, 2-Dimethyl	A		A		
Butane, 2, 3-Dimethyl	A		A		
Butanediol	C	A	B		
Butanol (Butyl Alcohol)	A	A	A		A
Butene 2-Ethyl (1-Butene 2-Ethyl)	A		A		
Butter-Animal Fat	A				A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Butyl Acetate or n-Butyl Acetate	D	A	A		C
Butyl Acetyl Ricinoleate	A		A		
Butyl Acrylate	D	C	A		
Butyl Alcohol	A	A	A		
Butyl Alcohol (Secondary)	A	A	A		
Butyl Alcohol (Tertiary)	A	A	A	D	
Butyl Amine or N-Butyl Amine	D	C	A		
Butyl Benzoate	C	A	A		
Butyl Benzoate or n-Butyl Benzoate	A		A		
Butyl Benzolate			A		
Butyl Butyrate or n-Butyl Butyrate	A	A	A		
Butyl Carbitol	C	A	A		
Butyl Cellosolve	D		A		
Butyl Cellosolve Acetate	C		A		
Butyl Cellosolve Adipate	B		A		
Butyl Chloride	A		A		
Butyl Ether or n-Butyl Ether	D		A		
Butyl Glycolate	C		A		
Butyl Lactate	C		A		
Butyl Laurate	C		A		
Butyl Mercaptan (Tertiary)	A		A		
Butyl Methacrylate	C		A		
Butyl Oleate	A		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Butyl Oxalate	C		A		
Butyl Stearate	A		A		
Butylbenzoic Acid	A		A		
Butylene	A	A	A		A
Butyraldehyde	D		B		
Butyric Acid	B		A		A
Butyric Anhydride	C		A		
Butyrolacetone	C		A		
Butyryl Chloride	A		A		
Cadmium Chloride	C		A		
Cadmium Cyanide	C	A	A		
Cadmium Nitrate	C		A		
Cadmium Oxide	C		A		
Cadmium Sulfate	C		A		
Cadmium Sulfide	C		A		
Calcine Liquors	A		A		
Calcium Acetate	D	A	A		
Calcium Arsenate	C		A		
Calcium Benzoate	A		A		
Calcium Bicarbonate	C	A	A		
Calcium Bisulfide	C	A	A		B
Calcium Bisulfite	B		A		A
Calcium Bromide	A		A		
Calcium Carbide		A	A		
Calcium Carbonate	A	A	A	A	A
Calcium Chlorate	C	A	A		A
Calcium Chloride	A	A	A	A	D
Calcium Chromate	C		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Calcium Cyanamide			A		
Calcium Cyanide		A	A		
Calcium Fluoride	A		A		
Calcium Gluconate	C		A		
Calcium Hydride	A		A		
Calcium Hydro-sulfide	C		A		
Calcium Hydroxide	A	A	A	A	A
Calcium Hypochlorite	A	A	A	A	C
Calcium Hypophosphite	C		A		
Calcium Lactate	C		A		
Calcium Naphthenate			A		
Calcium Nitrate	A	A	A	A	
Calcium Oxalate	C		A		
Calcium Oxide	A	A	A		
Calcium Permanganate			A		
Calcium Peroxide			A		
Calcium Phenol-sulfonate	C		A		
Calcium Phosphate	A	A	A		
Calcium Phosphate Acid	C		A		
Calcium Propionate	C		A		
Calcium Pyridine Sulfonate			A		
Calcium Salts	A	A	A	A	
Calcium Silicate	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Calcium Stearate	A	A	A		
Calcium Sulfamate	A		A		
Calcium Sulfate	C	A	A	A	A
Calcium Sulfide	A	A	A		
Calcium Sulfite	A	A	A		
Calcium Thiocyanate	C		A		
Calcium Thiosulfate	A	A	A		
Calcium Tungstate	C				
Caliche Liquors	A	A	A		
Camphene	A	A	A		
Camphor	A	A	A		
Camphoric Acid	A	A	A		
Cane Sugar Liquors	A	A	A		A
Capric Acid	A	A	A		
Caproic Acid	A	A	A		
Caproic Aldehyde	D	C	A		
Caprolactam	A	C	A		
Capronaldehyde	A		B		
Carbamate	A	A	A		
Carbazole			A		
Carbitol	B	B	A		
Carbolic Acid (Phenol)	A	A	A		
Carbon Bisulfide	A		A		
Carbon Dioxide	A	A	A		A
Carbon Dioxide (Explosive Decompression Use)	A	A	A		A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Carbon Disulfide	A	A	A	D	A
Carbon Fluorides	A		A		
Carbon Mon-oxide	A	A	A	A	A
Carbon Tetrabro-mide			A		
Carbon Tetra-chloride	A	A	A	D	B
Carbon Tetra-fluoride	A		B		
Carbonic Acid	A	A	A	A	B
Casein	C	A	A		
Castor Oil	A	A	A	C	
Caustic Lime	C	A	A		
Caustic Potash	C	A	A		
Caustic Soda (Sodium Hydroxide)	C	B	A		
Cellosolve	D	C	A	C	
Cellosolve, Ace-tate	D	C	A	C	
Cellosolve, Butyl	D		A		
Cellugard	A	A			
Cellulose Acetate	C	B	A		
Cellulose Acetate Butyrate	C		A		
Cellulose Ether	C		A		
Cellulose Nitrate*	C		A		
Cellulose Tripro-pionate	C		A		
Cellulube (Phos-phate Esters)		A	A		
Cellutherm 2505A	A	A			
Cerium Sulfate	C		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Cerous Chloride	C		A		
Cerous Fluoride	C		A		
Cerous Nitrate	C		A		
Cetane (Hexadecane)	A	A	A		
Cetyl Alcohol	A	A	A		
Chaulmoogric Acid			A		
China Wood Oil (Tung Oil)	A	A	A		
Chloral	C	C	A		
Chloramine		C	A		
Chloranthraquinone	A		A		
Chlordane	A	A	A		
Chlorextol	A	A	A		
Chloric Acid	C		A		D
Chlorinated Solvents, Dry	A	A	A		
Chlorinated Solvents, Wet	A	A	A		A
Chlorine (Dry)	A	A	A		A
Chlorine (Plasma)		A	B		
Chlorine (Wet)		A	B		A
Chlorine Dioxide	A	A	A		
Chlorine Dioxide, 8% Cl as NaClO ₂ in solution	A	A	B		
Chlorine Tri-fluoride	D	C	B		
Chlorine Water	A	A	A		
Chloro 1-Nitro Ethane (1-Chloro 1-Nitro Ethane)	D	C			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Chloro Oxyfluorides			B		
Chloro Xylenols	A		A		
Chloroacetaldehyde	C	C	B		
Chloroacetic Acid	D	B	A	B	
Chloroacetone	D	B	A		
Chloroacetyl Chloride			A		
Chloroamino Benzoic Acid	C		A		
Chloroaniline	C		A		
Chlorobenzaldehyde	C	C	A		
Chlorobenzene	A	A	B	D	A
Chlorobenzene (Mono)	A		A		
Chlorobenzene Chloride	A		A		
Chlorobenzene Trifluoride	A		A		
Chlorobenzo-chloride	A		A		
Chlorobenzotrifluoride	A		A		
Chlorobromo Methane	A	A	A		
Chlorobromopropane	A	A	A		
Chlorobutadiene	A	A	A		
Chlorobutane (Butyl Chloride)	A	A	A		
Chlorododecane	A	A	A		
Chloroethane	A	A	A		
Chloroethane Sulfonic Acid	C		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Chloroethylbenzene	A	A	A		
Chloroform	A	A	A	C	A
Chlorohydrin	C		A		
Chloronaphthalene or o-Chloronaphthalene	A	A	A		
Chloronitrobenzene	C		A		
Chlorophenol or o-Chlorophenol	A	A	A		
Chloropicrin	A	A	A		
Chloroprene	A	A	A		
Chlorosilanes	X		A		
Chlorosulfonic Acid	D		A	D	
Chlorotoluene	A	A	A		
Chlorotoluene Sulfonic Acid	C		A		
Chlorotoluidine	A	B	A		
Chlorotrifluoroethylene (CTFE)			B		
Chlorox	A	A	A		A
Chloroxylols	X				
Cholesterol	A		A		
Chrome Alum	A	A	A		
Chrome Plating Solutions	A	A	A		
Chromic Acid	A	A	A	A	B
Chromic Chloride			A		
Chromic Fluorides			A		
Chromic Hydroxide			A		
Chromic Nitrates			A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Chromic Oxide	A	A	A		
Chromic Phosphate			A		
Chromic Sulfate			A		
Chromium Potassium Sulfate (Alum)	A		A		
Chromyl Chlorides			A		
Cinnamic Acid	A	A	A		
Cinnamic Alcohol	A	A	A		
Cinnamic Aldehyde	A	B	A		
Circo Light Process Oil	A		A		
Citric Acid	A	A	A	A	A
City Service #65 #120 #250	A				
City Service Koolmoter-AP Gear Oil 140-EP Lube	A				
City Service Pace-maker #2	A				
Clorox	A	A	A		
Coal Tar	A	A	A		
Cobalt Chloride	A	A	A		
Cobalt Chloride, 2N	A		A		
Cobaltous Acetate	C		A		
Cobaltous Bromide	A		A		
Cobaltous Linoleate			A		
Cobaltous Naphthenate			A		
Cobaltous Sulfate	C		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Coconut Oil	A	A	A	C	
Cod Liver Oil	A	A	A		
Codeine	A		A		
Coffee	A		A		
Coke Oven Gas	A	A	A		
Coliche Liquors			A		
Convelex 10					
Coolanol 20 25R 35R 40& 45A (Monsanto)	A		A		
Copper Acetate	D	C	A		
Copper Ammonium Acetate	C		A		
Copper Carbonate	C	A	A		
Copper Chloride	A	A	A	A	D
Copper Cyanide	A	A	A		A
Copper Gluconate	C		A		
Copper Naphthenate			A		
Copper Nitrate	A	A	A	A	A
Copper Oxide	A		A		
Copper Salts	A	A	A		
Copper Sulfate	A	A	A	A	A
Copper Sulfate 10%	A	A	A		B
Copper Sulfate 50%	A	A	A		
Corn Oil	A	A	A	A	
Cottonseed Oil	A	A	A		
Creosote, Coal Tar	A	A	A		
Creosote, Wood	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Cresol (Methyl Phenol)	A	A	A		
Cresols	B	A	A	D	A
Cresylic Acid	A	A	A	B	A
Crotonaldehyde	A	B	A		
Crotonic Acid	A	A	A		
Crude Oil	A	A	A		
Cumaldehyde	A		A		
Cumene	A	A	A		
Cumene Hydroperoxide			A		
Cupric Sulfate	A	A			
Cutting Oil	A	A	A		
Cyanamide			A		
Cyanides			A		
Cyanogen Chloride			B		
Cyanogen Gas			A		
Cyanohydrin			A		
Cyanuric Chloride			A		
Cyclohexane	A	A	A		A
Cyclohexanol	A	A	A		
Cyclohexanone	D	A	A	D	
Cyclohexene	A	B	A	D	
Cyclohexylamine	A	C	B		
Cyclohexylamine Carbonate			B		
Cyclohexylamine Laurate	A	C	B		
Cyclopentadiene	A	B	A		
Cyclopentane	A	A	A		
Cyclopolyolefins	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Cymene or p-Cymene	A	A	A		
DDT (Dichlorodiphenyltrichloroethane)	A	A	A		
Decalin	A	A	A		
Decane	A		A		
Delco Brake Fluid	A		A		
Denatured Alcohol	A	A	A		
Detergent, Water Solution	A	A	A		A
Developing Fluids (Photo)	A	A	A		
Dexron	A	A	A		
Dextrin	A	A	A		
Dextro Lactic Acid	C		A		
Dextron	A				
Dextrose	C	A	A		
DI Water	B	A	B		
Diacetone	D	B	A		
Diacetone Alcohol	D	B	A		
Dialkyl Sulfates	C		A		
Diallyl Ether		B	A		
Diallyl Phthalate		A	A		
Diamylamine	A	C	B		
Diazinon	B	A	A		
Dibenzyl (sym-Diphenylethane)	A	A	A		
Dibenzyl Ether Factory	D	C	A		
Dibenzyl Sebacate	B	A	A		
Diborane			A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Dibromoethane	A		A		
Dibromoethyl Benzene	A	A	A		
Dibutyl Cellosolve Adipate	C		A		
Dibutyl Ether Factory	C	B	A		
Dibutyl Methylene-dithio Glycolate	A		A		
Dibutyl Phthalate	C	A	A	A	
Dibutyl Sebacate	B	A	A		
Dibutyl Thioglycolate	A		A		
Dibutyl Thiourea	A		A		
Dibutylamine	D	C	A		
Dichloroacetic Acid	A	C	A		
Dichloroaniline	C	A	A		
Dichlorobenzene or o-Dichlorobenzene	A	A	A		
Dichlorobenzene or p-Dichlorobenzene	A	A	A		
Dichlorobutane	A	A	A		
Dichlorobutene	A	A	A		
Dichlorodiphenyl-Dichloroethane (DDD)	A		A		
Dichloroethane	A	A	A		A
Dichloroethylene	A	A	A		
Dichlorohydrin	C		A		
Dichloroisopropyl Ether	C	B	A		
Dichloromethane	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Dichlorophenol	A	A	A		
Dichlorophenoxy-acetic Acid	A		A		
Dichloropropane	A	A	A		
Dichloropropene	A	A	A		
Dichlorosilane			A		
Dicyclohexylamine	D	B	A		
Dicyclohexylammonium Nitrate	C				
Dieldrin	A	B	A		
Diesel Oil	A	A	A	D	A
Di-ester Lubricant MIL-L-7808	A	A	A		
Di-ester Synthetic Lubricants	A	A			
Diethanolamine (DEA)	C	B		A	
Diethyl Benzene	A	A	A		
Diethyl Carbonate	C	B	A		
Diethyl Ether	D	B	A		
Diethyl Phthalate	A		A		
Diethyl Sebacate	B		A		
Diethyl Sulfate	C		A		
Diethylamine	D		B		A
Diethylaniline	C		A		
Diethylene Glycol	A	A	A	A	A
Diethylenetriamine		C	A		
Difluorodibromomethane			A		
Difluoroethane	A	D	A		
Difluoromono-chloroethane	A		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Diglycol Chloroformate	C		A		
Diglycolic Acid	C		A		
Dihydroxydiphenylsulfone	C		A		
Diisobutyl Ketone		C	A		
Diisobutylcarbinol	A		A		
Diisobutylene	A		A		
Diisooctyl Sebacate 3 2	B				
Diisopropyl Ether (DIPE)		A	A		
Diisopropyl Ketone	D	C	A		
Diisopropylbenzene	A		A		
Diisopropylidene Acetone	A	C	A		
Dimethyl Acetamide	C	A	A		
Dimethylaniline (Xylidine)	A	B	A		
Dimethyldisulfide (DMDS)	A		A		
Dimethyl Ether	B	C	A		
Dimethyl Formaldehyde	C	C	A		
Dimethyl Formamide (DMF)	D	A	A	B	
Dimethylhydrazine	C	B	A		
Dimethyl Phenyl Carbinol	A		A		
Dimethyl Phenyl Methanol	A		A		
Dimethyl Phthalate	B	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Dimethyl Sulf-oxide (DMSO)	C	C	A	D	
Dimethyl Terephthalate (DMT)	A	A	A		
Dimethylamine (DMA)	D		B		
Dinitrochlorobenzene	A		A		
Dinitrogen Tetroxide			B		
Dinitrotoluene (DNT)	D		A		
Diethyl Phthalate	B	A	A	A	
Diethyl Sebacate	B	A	A		
Diethylamine	A		A		
Dioxane	D	C	A	D	
Dioxolane	D	C	A		
Dipentene	A	A	A		
Diphenyl	A	A	A	A	
Diphenyl Oxides	A	A	A		
Diphenylamine (DPA)	A		A		
Diphenylene Oxide		A	A		
Diphenylpropane	A	A	A		
Disilane		A			
Di-Tert-Butyl Peroxide			A		
Dodecylbenzene	A	A	A		
Dow Chemical 50-4	D	A			
Dow Chemical ET378					
Dow Chemical ET588	D				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Dow Corning -11	A				
Dow Corning -1208, 4050, 6620, F-60, XF-60	A	A			
Dow Corning -1265 Fluorosilicone Fluid	A				
Dow Corning -200	A	A			
Dow Corning -220	A	A			
Dow Corning -3	A	A			
Dow Corning -33	A	A			
Dow Corning -4	A	A			
Dow Corning -44	A	A			
Dow Corning -5	A	A			
Dow Corning -510	A	A			
Dow Corning -55	A	A			
Dow Corning -550	A	A			
Dow Corning -704	A	A			
Dow Corning -705	A	A			
Dow Corning -710	A	A			
Dow Corning F-61	A	A			
Dow Guard	A	A			
Dowanol P Mix			A		
Dowtherm, 209	D	A	A		
Dowtherm, A	A	A	A		
Dowtherm, E	A	A	A		
Drinking Water	A	A	A	A	

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Dry Cleaning Fluids	A	A	A		
DTE 20 Series, Mobil	A	A	A		
DTE named series, Mobil, light-heavy	A	A	A		
Elco 28-EP lubricant	A	A			
Epichlorohydrin	D	C	B		
Epoxy Resins	D	B	A		
Erucic Acid					
Esam-6 Fluid	D	B			
Esso Fuel 208	A	A			
Esso Golden Gasoline	A	A			
Esso Motor Oil	A	A			
Esso Transmission Fluid (Type A)	A	A			
Esso WS2812 (MIL-L-7808A)	A	A			
Esso XP90-EP Lubricant	A	A			
Esstic 42, 43	A	A			
Ethane	A	A	A		A
Ethanol	C	A	A		A
Ethanol Amine	D	C	A		A
Ethers	C	C	A	C	A
Ethoxyethyl Acetate (EGMEEA)	C				A
Ethyl Acetate-Organic Ester	D	B	A	B	
Ethyl Acetoacetate	D	C	A		
Ethyl Acrylate	D	C	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Ethyl Alcohol	C	A	A	A	
Ethyl Ammonium Dichloride					
Ethyl Benzene	A	A	A		
Ethyl Benzoate	A	A	A	D	
Ethyl Bromide	A	A	A	D	
Ethyl Cellosolve	D	B	A		
Ethyl Cellulose	D	C	A		
Ethyl Chloride	A	A	A	C	A
Ethyl Chlorocarbonate	A	A	A		
Ethyl Chloroformate	D		A		
Ethyl Ether	D	C	A	C	
Ethyl Formate	A	A	A		
Ethyl Hexanol	A	A	A		
Ethyl Lactate	C				
Ethyl Mercaptan X 2	B	A	A		
Ethyl Nitrite	C				
Ethyl Oxalate	B	A	A		
Ethyl Pentachlorobenzene	A	A	A		
Ethyl Pyridine	A				
Ethyl Silicate	A	A	A		
Ethyl Stearate	A				
Ethyl Sulfate	D		A		D
Ethyl Tertiary Butyl Ether		A			
Ethyl Valerate	A				
Ethylacrylic Acid					
Ethylamine	C				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Ethylcyclopentane	A	A			
Ethylene	B	A	A		
Ethylene Chloride	B	A	A		A
Ethylene Chlorohydrin	A	A	A	A	
Ethylene Cyano- hydrin	A				
Ethylene Diamine	D	A	B		
Ethylene Dibromide	A	A	A		
Ethylene Dichloride	A	A	A	C	A
Ethylene Glycol	A	A	A	A	A
Ethylene Hydrochloride	A				
Ethylene Oxide	D	D	A	A	A
Ethylene Oxide, (12%) and Freon 12 (80%)	D				
Ethylene Trichloride	A	A	A		
Ethyleneimine					
Ethylmorpholene Stannous Octo- tate (50/50 mixture)	D				
Ethylmorpholine	A				
Ethylsulfuric Acid	C				
F-60 Fluid (Dow Corning)	A	A			
F-61 Fluid (Dow Corning)	A	A			
Fatty Acids	A	A	A		
FC-43 Heptacosofluorotri-butylamine	A				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
FC75 & FC77 (Fluorocarbon)	B				
Ferric Acetate	C	C			
Ferric Ammonium Sulfate	C				
Ferric Chloride	A	A	A	A	
Ferric Ferrocyanide	C				
Ferric Hydroxide	C	A	A		
Ferric Nitrate	A	A	A	A	A
Ferric Persulfate	A				
Ferric Sulfate	A	A	A		A
Ferrous Ammonium Citrate	C				
Ferrous Ammonium Sulfate	C	A			
Ferrous Carbonate	C				
Ferrous Chloride		A	A		D
Ferrous Iodide	C				
Ferrous Sulfate	C	A	A		C
Ferrous Tartrate	C				
Fish Oil	A	A	A		
Fisher Reagent					
Fluorinated Cyclic Ethers					
Fluorine (Gas)		A	B	D	
Fluorine (Liquid)	B	A	B		D
Fluorobenzene	A	A	A		
Fluoroboric Acid					
Fluorocarbon Oils					
Fluoroform (Trifluoromethane)					
Fluorolube	B		B		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Fluorophosphoric Acid					
Fluorosilicic Acid	B	A	A		B
Fluorosulfonic Acid					
Formaldehyde	D	C	A	D	A
Formamide	C		A		
Formic Acid	D	C	B		B
Freon, 11	B	B	B	A	A
Freon, 112 (Tetra-chlorodifluoroethane)	A	B	B		
Freon, 113	B	C	C		A
Freon, 113 + High and Low Aniline Oil		C			
Freon, 114	A	B	C		
Freon, 114B2	B	B	C		
Freon, 115, 116	B	B	C		
Freon, 12	C	B	B	A	D
Freon, 12 and ASTM Oil #2 (50/50 Mixture)	A	B			
Freon, 12 and Suniso 4G (50/50 Mixture)	A	B			
Freon, 123 (Dichlorotrifluoroethane)					
Freon, 124 (Chlorotetrafluoroethane)					
Freon, 125 (Pentafluoroethane)					
Freon, 13	A		A		
Freon, 134a (Tetrafluoroethane)			B		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Freon, 13B1	A		B		
Freon, 14	A		A		
Freon, 141b (Dichlorofluoroethane)					
Freon, 142b	B				
Freon, 152a (Difluoroethane)					
Freon, 21	D	D	B		
Freon, 218	A				
Freon, 22 (Chlorodifluoroethane)	D	D	B	A	A
Freon, 22 and ASTM Oil #2 (50/50 Mixture)	B	D	B		
Freon, 23 (Fluoroform)					
Freon, 31	D	D	B		
Freon, 32	D	D	B		
Freon, 502	B		C		
Freon, BF (R112)	A	B			
Freon, C316	A	B	B		
Freon, C318	B	B	C		
Freon, K-142b	D		C		
Freon, K-152a	D		C		
Freon, MF (R11)	B				
Freon, PCA (R113)	B		C		
Freon, TA	D	D	C		
Freon, TC	B	B	B		
Freon, TF (R113)	B	B			A
Freon, TMC	B	B	B		
Freon, T-P35	B	B	B		
Freon, T-WD602	A	B	B		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Fuel Oil, #6	A	A	A	A	A
Fuel Oil, 1, and 2	A				A
Fuel Oil, Acidic	A				A
Fumaric Acid	A	A	A		
Fuming Sulphuric Acid (20/25% Oleum)	A				
Furaldehyde	D	C			
Furan (Furfuran)	C	C	A		A
Furfural (Furfuraldehyde)	D	C	B	D	A
Furfuraldehyde	D	C			
Furfuryl Alcohol	B	A	A		
Furoic Acid					
Furyl Carbinol					
Fyrquel 150 220 300 550	A	A			
Fyrquel 90, 100, 500	A	A			
Fyrquel A60	D	A			
Gallic Acid	A	A	A	B	A
Gasoline	A	A	A		A
Gelatin	A	A	A	A	A
Germane (Germanium Tetrahydride)					
Girling Brake Fluid	D	B			
Glauber's Salt	A	A	A		
Gluconic Acid	C	B	A		
Glucose	A	A	A	A	A
Glue		A			A
Glutamic Acid	C	B			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Glycerine (Glycerol)	A	A	A	A	A
Glycerol Dichlorohydrin	C				
Glycerol Monochlorohydrin	C				
Glycerol Triacetate	C				
Glycerophosphoric Acid	C				
Glyceryl Phosphate	C				
Glycidol	C				
Glycol Monoether					
Glycolic Acid	C		A	B	
Glycols	A	A	A		
Glyoxylic Acid	C				
Grease Petroleum Base	A		A		A
Green Sulfate Liquor	A	A	B		
Gulf Endurance Oils	A	A			
Gulf FR Fluids (Emulsion)	A				
Gulf FR G-Fluids	A				
Gulf FR P-Fluids	B				
Gulf Harmony Oils	A				
Gulf High Temperature Grease	A				
Gulf Legion Oils	A				
Gulf Paramount Oils	A				
Gulf Security Oils	A				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Gulfcrown Grease	A				
Halothane	A	A	B		
Halowax Oil	A	A	B		
Hannifin Lube A	A				
Heavy Water		A	A		
HEF-2 (High Energy Fuel)	A	A	A		
Helium	A	A	A		
Heptachlor	A	A			
Heptachlorobutene	A				
Heptaldehyde (Heptanal)	D	C			
Heptane or n-Heptane	A	A	A	D	A
Heptanoic Acid	A	A			
Hexachloroacetone	C	B			
Hexachlorobutadiene	A		A		
Hexachlorobutene	A				
Hexachloroethane	A	A			
Hexaethyl Tetraphosphate					
Hexafluoroethane (F-116)					
Hexafluoroxylene					
Hexaldehyde or n-Hexaldehyde	D	C			
Hexamethyldisilazane					
Hexamethylene (Cyclohexane)	A				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Hexamethylene Diammonium Adipate	A				
Hexamethylene-diamine	C				
Hexamethylene-tetramine	C	C			
Hexane or n-Hexane	A	A	A	D	A
Hexene-1 or n-Hexene-1	A	A			
Hexone (Methyl Isobutyl Ketone)	C	C	A		
Hexyl Acetate	C	C			
Hexyl Alcohol	A	A	A		
Hexylene Glycol	C	A	A		
Hexylresorcinol	A	A			
High Viscosity Lubricant, H2	A	A			
High Viscosity Lubricant, U4	A	A			
HiLo MS #1	D				
Houghto-Safe 1010 phosphate ester	A	A			
Houghto-Safe 1055 phosphate ester	A	A			
Houghto-Safe 1120 phosphate ester	A	A			
Houghto-Safe 271 (Water & Glycol Base)	B	A			
Houghto-Safe 416 & 500 Series		A			
Houghto-Safe 5040 (Water/Oil emulsion)	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Houghto-Safe 620 Water/Glycol	B	A			
Hydraulic Oil (Petroleum Base, Industrial)	A	A	A		A
Hydraulic Oils (Synthetic Base)	A	A	A		A
Hydrazine	D	C	A	C	A
Hydrazine (Anhydrous)	D	C	B		
Hydrazine Dihydrochloride	C				
Hydrazine Hydrate	C	C			
Hydriodic Acid	A	A			
Hydroabietyl Alcohol					
Hydrobromic Acid	A	A	A		D
Hydrobromic Acid 40%	A				D
Hydrocarbons, Saturated	A				
Hydrochloric Acid (cold) 37%	A	A	A	A	A
Hydrochloric Acid (hot) 37%	A	A	A	A	D
Hydrochloric Acid, 3 Molar to 158°F	A	A	A	A	D
Hydrochloric Acid, Concentrated Room Temp.	A	A	A	A	D
Hydrochloric Acid, Concentrated to 158°F	A	A	A	A	D
Hydrocyanic Acid	A	A	A	A	A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Hydro-Drive MIH-10 (Petroleum Base)	A				
Hydro-Drive MIH-50 (Petroleum Base)	A				
Hydrofluoric Acid (Anhydrous)		C	A	D	D
Hydrofluoric Acid (conc.) Cold		C		D	D
Hydrofluoric Acid (conc.) Hot 4 3	C	C		D	D
Hydrofluorosilicic Acid	A	A	A		D
Hydrogen Bromide (Anhydrous)			A		
Hydrogen Chloride (Anhydrous)			A		
Hydrogen Chloride gas	A				
Hydrogen Cyanide		A			
Hydrogen Fluoride			A		
Hydrogen Fluoride (Anhydrous)	D	C	A		
Hydrogen Gas, Cold	A		A	A	A
Hydrogen Gas, Hot	A				
Hydrogen Iodide (Anhydrous)					
Hydrogen Peroxide	A	A	A	A	C
Hydrogen Peroxide 90%	A	A	A		B
Hydrogen Selenide					

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Hydrogen Sulfide, Dry, Cold	D	C	A	A	A
Hydrogen Sulfide, Dry, Hot	D	C			A
Hydrogen Sulfide, Wet, Cold	D	C	A		A
Hydrogen Sulfide, Wet, Hot	D	C			A
Hydrolube-Water/Ethylene Glycol	A	A	A		
Hydrooxycitronellal	A				
Hydroquinol	A				
Hydroquinone	B	A	B		
Hydroxyacetic Acid	C	B	A		
Hydyne	D	D			
Hyjet	D	C			
Hyjet IV and IVA	D	C			
Hyjet S4	D	C			
Hyjet W	D	C			
Hypochlorous Acid	A	A	A		
Indole	A		A		
Industron FF44	A				
Industron FF48	A				
Industron FF53	A				
Industron FF80	A				
Insulin	C				
Iodic Acid	C				
Iodine	A	A			C
Iodine Penta-fluoride	D	C	B		
Iodoform	B	B	A		A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Isoamyl Acetate	C	C	A		
Isoamyl Butyrate	C	B	A		
Isoamyl Valerate	C	A			
Isoboreol	A				
Isobutane	A	A	A		A
Isobutyl Acetate	C	C			
Isobutyl Alcohol	A	A	A	C	A
Isobutyl Chloride	A	A	A		
Isobutyl Ether	D	C			
Isobutyl Methyl Ketone	C	C			
Isobutyl n-Butyrate	A				
Isobutyl Phosphate	C				
Isobutylene	A	A			
Isobutyraldehyde	D				
Isobutyric Acid	D	B			
Isocrotyl Chloride	A				
Isodecanol	A	A			
Isododecane	A	A			
Isoeugenol	A	A			
Isooctane	A	A	A	D	A
Isopentane	A	A	A		
Isophorone (Ketone)	D	A	A		
Isopropanol	A	A	A		
Isopropyl Acetate	D	B	A	B	A
Isopropyl Alcohol	A	A	A	C	A
Isopropyl Chloride	A	A	A		
Isopropyl Ether	D	C	A	C	A
Isopropylacetone	C	B			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Isopropylamine	C	B			
Jet Fuel A	A	A		D	A
JP-10	A	A			
JP-3 (MIL-J-5624)	A	A			A
JP-4 (MIL-T-5624)	A	A			A
JP-5 (MIL-T-5624)	A	A			A
JP-6 (MIL-J-25656)	A	A			A
JP-8 (MIL-T-83133)	A	A			
JP-9 (MIL-F-81912)	A	A			
JP-9 -11	A	A			
JPX (MIL-F-25604)	D	C			
Kel F Liquids	B		B		
Kerosene (Similar to RP-1 and JP-1)	A	A	A		A
Ketones				D	A
Keystone #87HX-Grease	A				
Lacquer Solvents	D	B	A		A
Lacquers	D	B	A		A
Lactams-Amino Acids	D	A	A		
Lactic Acid, Cold	A	A	A	A	A
Lactic Acid, Hot	A	A	A	B	A
Lactones (Cyclic Esters)	D				
Lard Animal Fat	A	A	A	C	A
Lauric Acid	A	A			A
Lavender Oil	A	A			A
LB 135	A				
Lead (Molten)					

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Lead Acetate	D	B	A		A
Lead Arsenate	C				
Lead Azide					
Lead Bromide	C				
Lead Carbonate	C				
Lead Chloride	C	A	A		
Lead Chromate	C		A		
Lead Dioxide	C	A			
Lead Linoleate	C				
Lead Naphthenate					
Lead Nitrate		A	A		A
Lead Oxide	C	A			
Lead Sulfamate	A		A		
Lehigh X1169	A				
Lehigh X1170	A				
Light Grease	A		A		
Ligroin (Petroleum Ether or Benzene)	A	A	A		A
Lime Bleach	A	A	A		
Lime Sulfur	A	A	A		A
Lindol, Hydraulic Fluid (Phosphate ester type)	B	A	A		
Linoleic Acid	B	A	A	C	B
Linseed Oil	A	A	A	C	A
Liquid Oxygen (LOX)	D	D			
Liquid Petroleum Gas (LPG)	A	A	A		
Liquimoly	A		A		
Lithium Bromide (Brine)	C	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Lithium Carbonate	C				
Lithium Chloride	C	A	A		A
Lithium Citrate	C				
Lithium Hydroxide	C	B	A		A
Lithium Hypochlorite	C				
Lithium Nitrate	C				
Lithium Nitrite	C				
Lithium Perchlorate	C				
Lithium Salicylate	C				
Lithopone	C		A		
Lubricating Oils (Crude & Refined)	A	A	A		A
Lubricating Oils (Synthetic base)	A	A	A		A
Lubricating Oils, Di-ester	A	A			A
Lubricating Oils, petroleum base	A	A			A
Lubricating Oils, SAE 10, 20, 30, 40, 50	A	A			A
Lye Solutions	B	A	A		
Magnesium Chloride	A	A	A	A	C
Magnesium Hydroxide	A	A	A	A	A
Magnesium Salts	A	A	A	A	
Magnesium Sulfite and Sulfate	A	A	A	A	A
Magnesium Trisilicate	X				
Malathion	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Maleic Acid	A	A	A	C	A
Maleic Anhydride	D	B	A		
Maleic Hydrazide	C				
Malic Acid	A	A	A		A
Mandelic Acid	C	C			
Manganese Acetate	C	B			
Manganese Carbonate	C		A		
Manganese Chloride	C	A	A		
Manganese Dioxide	C				
Manganese Gluconate	C				
Manganese Hypophosphite	C				
Manganese Linoleate	C				
Manganese Naphthenate	C				
Manganese Phosphate	C				
Manganese Salts		A		A	
Manganese Sulfate	C	A	A		A
Manganous Chloride	C				
Manganous Phosphate	C				
Manganous Sulfate	C	A			
Mannitol	C				
MCS 312	A				
MCS 352	D				
MCS 463	D				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
MDI (Methylene di-p-phenylene isocyanate)	C				
Mercaptan	A	B			
Mercaptobenzothiazole (MBT)	A				
Mercuric Acetate	C	B			
Mercuric Chloride	A	A	A		C
Mercuric Cyanide	C	A	A		A
Mercuric Iodide	C				
Mercuric Nitrate	C		A		
Mercuric Sulfate	C	A			
Mercuric Sulfite	C				
Mercurous Nitrate	C	A			
Mercury	A	A	A	A	A
Mercury Chloride	C			A	
Mercury Fulminate	C				
Mercury Salts	C			A	
Mercury Vapors	A				
Mesityl Oxide (Ketone)	D	C	A		
Meta-Cresol	A				
Metaldehyde	C	C			
Meta-Nitroaniline	C				
Meta-Toluidine	A				
Methacrylic Acid	C		A		
Methallyl Chloride	A				
Methane	A	A			A
Methanol	D	A		A	A
Methoxychlor					

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Methoxyethanol (DGMMA)	C				
Methyl Abietate	A	A			
Methyl Acetate	D	B	A	B	A
Methyl Acetoacetate	D	B	A		
Methyl Acetophenone*	A	B			
Methyl Acrylate	D	C	A		
Methyl Alcohol	D	A	A		
Methyl Amylketone	C	B			
Methyl Anthranilate	A	A			
Methyl Benzoate	A	A	A		
Methyl Bromide	A	A	A	C	B
Methyl Butyl Ketone	D	B	A		A
Methyl Butyrate Cellosolve	C		A		
Methyl Butyrate Chloride	C				
Methyl Carbonate	A	A	A		
Methyl Cellosolve	D	B	A		A
Methyl Cellulose	D	B	A		
Methyl Chloride	A	A	A	C	A
Methyl Chloroacetate	C	B			
Methyl Chloroform	A	A			A
Methyl Chloroformate	A	A	A		
Methyl Chlorosilanes					

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Methyl Cyanide (Acetonitrile)	C		A		
Methyl Cyclohexanone	A	C			
Methyl Dichloride	A		A		
Methyl Ether	A	B	A		
Methyl Ethyl Ketone (MEK)	D	B	A	D	A
Methyl Ethyl Ketone Peroxide	D		A		
Methyl Ethyl Oleate	A				
Methyl Formate		B	A		A
Methyl Hexyl Ketone (2-Octanone)	C	B			
Methyl Iodide	A		A		
Methyl Isobutyl Ketone (MIBK)	D	B	A	D	A
Methyl Isocyanate	C	B			
Methyl Isopropyl Ketone	D	B			A
Methyl Isovalerate	A				
Methyl Lactate	C				
Methyl Mercaptan		A	A		
Methyl Methacrylate	D	B	A	D	
Methyl Oleate	A	A	A		
Methyl Pentadiene	A				
Methyl Phenylacetate	A	B			
Methyl Salicylate		A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Methyl Tertiary Butyl Ether (MTBE)	C	B			
Methyl Valerate	A				
N-Methyl-2-Pyrrolidone (NMP)	C		A	A	
Methylacrylic Acid	C				
Methylal					
Methylamine	C				A
Methylamyl Acetate	C				
Methylcyclopentane	A				
Methylene Bromide	A		A		
Methylene Chloride	B		A	C	A
Methylene Iodide	A				
Methylglycerol	C				
Methylisobutyl Carbinol	A				
Methylpyrrolidine	A				
Methylpyrrolidone	A				
Methylsulfuric Acid	C				
MIL-A-6091	A	A			
MIL-C-4339	A	A			
MIL-C-7024	A	A			
MIL-C-8188	B	A			
MIL-E-9500	A	A			
MIL-F-16884	A	A			
MIL-F-17111	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
MIL-F-25558 (RJ-1)	A	A			
MIL-F-25656	A	A			
MIL-F-5566	A	A			
MIL-F-81912 (JP-9)	A	A			
MIL-F-82522 (RJ-4)	A	A			
MIL-G-10924	A	A			
MIL-G-15793	A	A			
MIL-G-21568	A	A			
MIL-G-25013	A	A			
MIL-G-25537	A	A			
MIL-G-25760	A	A			
MIL-G-3278	A	A			
MIL-G-3545	A	A			
MIL-G-4343	A	A			
MIL-G-5572	A	A			
MIL-G-7118	A	A			
MIL-G-7187	A	A			
MIL-G-7421	A	A			
MIL-G-7711	A	A			
MIL-H-13910	A	A			
MIL-H-19457	A	A			
MIL-H-22251		A			
MIL-H-27601	A	A			
MIL-H-46170 -15°F to +400°F	A	A			
MIL-H-46170 -20°F to +275°F	A	A			
MIL-H-46170 -55°F to +275°F	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
MIL-H-46170 -65°F to +275°F	A	A			
MIL-H-5606 -65°F to +235°F	A	A			
MIL-H-5606 -65°F to +275°F	A	A			
MIL-H-6083	A	A			
MIL-H-7083	B	A			
MIL-H-8446 (MLO-8515)	A	A			
MIL-J-5161	A	A			
Milk	A	A			A
MIL-L-15016	A	A			
MIL-L-15017	A	A			
MIL-L-17331	A	A			
MIL-L-2104	A	A			
MIL-L-21260	A	A			
MIL-L-23699	A	A			
MIL-L-25681	A	A			
MIL-L-3150	A	A			
MIL-L-6081	A	A			
MIL-L-6082	A	A			
MIL-L-6085	A	A			
MIL-L-6387	A	A			
MIL-L-7808	A	A			
MIL-L-7870	A	A			
MIL-L-9000	A	A			
MIL-L-9236	A	A			
MIL-O-3503	A	A			
MIL-P-27402		A			
MIL-R-25576 (RP-1)	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
MIL-S-3136, Type I Fuel	A	A			
MIL-S-3136, Type II Fuel	A	A			
MIL-S-3136, Type III Fuel	A	A			
MIL-S-3136, Type IV Oil High Swell	A	A			
MIL-S-3136, Type IV Oil Low Swell	A	A			
MIL-S-3136, Type V Oil Medium Swell	A	A			
MIL-S-81087	A	A			
MIL-T-5624, JP-4, JP-5	A	A			
MIL-T-83133	A	A			
Mineral Oils	A	A	A		A
Mixed Acids	C				
MLO-7277 Hydr.	A	A			
MLO-7557	A	A			
MLO-8200 Hydr.	A	A			
MLO-8515	A	A			
Mobil 24dte	A	A			
Mobil 254 Lubricant		A			
Mobil Delvac 1100, 1110, 1120, 1130	A	A			
Mobil HF	A	A			
Mobil Nivac 20, 30	A	A			
Mobil SHC 500 Series	A	A			
Mobil SHC 600 Series	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Mobil Therm 600	A	A			
Mobil Velocite c	A	A			
Mobilgas WA200 ATF	A	A			
Mobilgear 600 Series	A	A			
Mobilgear SHC ISO Series	A	A			
Mobilgrease HP	A	A			
Mobilgrease HTS	A	A			
Mobilgrease SM	A	A			
Mobilith AW Series	A	A			
Mobilith SHC Series	A	A			
Mobiljet II Lubricant		A			
Mobilmistlube Series	A	A			
Mobiloil SAE 20	A	A			
Mobilux	A				
Molybdenum Disulfide Grease	A	A			
Molybdenum Oxide	C				
Molybdenum Trioxide	C				
Molybdic Acid	C				
Monobromobenzene	A	A	A		
Monobromotoluene	A				
Monobutyl Paracresol					
Monochloroacetic Acid	C	B	A		C

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Monochlorobenzene	A	A	A		A
Monochlorobutene	A				
Monochlorohydrin					
Monoethanolamine (MEA)	D		A	C	A
Monoethyl Amine	C		A		
Monoisopropylamine	C		A		
Monomethyl Aniline	B				
Monomethyl Ether (Dimethyl Ether)			A		
Monomethyl Ether (Methyl Ether)	A	A	A		
Monomethyl Hydrazine			A		
Monomethylamine (MMA)	C				
Monomethylaniline	B	A			
Mononitrotoluene	C				
Mononitrotoluene & Dinitrotoluene (40/60 Mixture)	C				
Monovinyl Acetylene	A	A			
Mopar Brake Fluid	D				
Morpholine	A		A		B
Motor Oils	A			D	A
Mustard Gas		A	A		A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Myristic Acid	A	A			
Naphthalene	A	A	A	D	A
Naphthalene Chloride	A	A			B
Naphthalene Sul-fonic Acid	A				
Naphthalenic Acid	A	A	A		
Naphthalonic Acid	A				
Naphthenic Acid	A				
Naphthylamine	C	A			
Naptha	A			D	A
Natural Gas	A	A	A		A
Neatsfoot Oil	A		A		
Neon	A	A	A		
Neville Acid	A	A	A		
Nickel Acetate	D	B	A		
Nickel Ammo-nium Sulfate	C	A			A
Nickel Chloride	A	A	A	A	A
Nickel Cyanide	C				
Nickel Nitrate	C	A	A	A	A
Nickel Salts	A		A	A	
Nickel Sulfate	A	A	A	A	B
Nicotinamide (Niacinamide)	A				
Nicotinamide Hydrochloride	C				
Nicotine	A	A			A
Nicotine Sulfate	C				
Niter Cake	A	A	A		
Nitric Acid, Red Fuming	B	A	B		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Nitric Acid, White Fuming		A			
Nitric Acid (0 - 50%)	A	A		A	A
Nitric Acid (50 - 100%) 4 3	C	A			B
Nitric Acid 3 Molar to 158°F	C	A	A		
Nitric Acid Concentrated Room Temp.	B	A	A		B
Nitric Acid Concentrated to 158°F	D	A			C
Nitroaniline	C				
Nitrobenzene	B	A	A	D	B
Nitrobenzoic Acid	C				
Nitrocellulose	C				
Nitrochlorobenzene	C				
Nitrochloroform	C				
Nitrodiethylaniline	C				
Nitrodiphenyl Ether					
Nitroethane	D	C	A		
Nitrofluorobenzene	C				
Nitrogen	A	A	A		A
Nitrogen Oxides	C	C			
Nitrogen Tetroxide (N ₂ O ₄)	D	C	A		
Nitrogen Trifluoride					
Nitroglycerine	C				A
Nitroglycerol	C				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Nitroisopropylbenzene	C				
Nitromethane	D		A	D	
Nitrophenol	C	C			
Nitropropane	D	C	A		
Nitrosyl Chloride					
Nitrosylsulfuric Acid					
Nitrothiophene	C				
Nitrotoluene	C	B			
Nitrous Acid	C		A	A	B
Nitrous Oxide	A	B			A
Nonane	A	A			
Noryl GE Phenolic					
Nyvac FR200 Mobil	A				
Octachloro Toluene	A	A	A		
Octadecane	A	A	A		
Octanal (n-Octanaldehyde)	A	C	A		
Octane or n-Octane	A	A			A
Octyl Acetate	C	B	A		
Octyl Alcohol	A	A	A		
Octyl Chloride	A	A			
Octyl Phthalate	A	A			
Olefins	A	A			
Oleic Acid	B	A	A	C	A
Oleum (Fuming Sulfuric Acid)	A	A	A	A	A
Oleum Spirits	A	A			
Oleyl Alcohol	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Olive Oil	A	A	A	A	A
Oronite 8200	A	A			
Oronite 8515	A	A			
Ortho-Chloro Ethyl Benzene	A	A	A		
Ortho-Chloroaniline	C				
Ortho-Chlorophenol	C				
Ortho-Cresol	C				
Ortho-Dichlorobenzene	A			D	
Ortho-Nitrotoluene	C				
Orthophos Acid					
OS 45 Type III (OS45)	A	A			
OS 45 Type IV (OS45-1)	A	A			
OS 70	A	A			
Oxalic Acid	A	A	A	B	B
Oxygen, 200°-300°F (Evalute for specific applications)	B	A	A		A
Oxygen, 300°-400°F (Evalute for specific applications)	B	A	A		A
Oxygen, Cold (Evalute for specific applications)	A	A		A	A
Oxygen, Liquid	D	D	D		A
Ozonated Deionized Water	C				
Ozone	A	A	A	A	A
Paint Thinner, Duco	B	A	A	B	

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Palmitic Acid	A	A	A	C	A
Para-Aminobenzoic Acid	C				
Para-Bromobenzylphenyl Ether					
Para-Chlorophenol	C				
Paracymene	A				
Para-Dichlorobenzene	A		A		
Paraffins	A	A	A	D	A
Para-Formaldehyde	C				
Paraldehyde	C	C	A		
Par-al-Ketone	D	C	A		
Para-Nitroaniline	C				
Para-Nitrobenzoic Acid	C				
Para-Nitrophenol	C				
Parathion	A				
Para-Toluene Sulfonic Acid	C				
Parker O Lube	A				
Peanut Oil	A	A	A		A
Pectin (Liquor)	A				
Pelagonic Acid	A				
Penicillin (Liquid)	A		A		
Pentachloroethane	A	A	A		
Pentachlorophenol	C	A	A		
Pentaerythritol	C				
Pentaerythritol Tetranitrate	C				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Pentafluoroethane (F-125)					
Pentane or n-Pentane	A	A	A		A
Pentane, 2 Methyl	A				
Pentane, 2-4 dimethyl	A				
Pentane, 3-Methyl	A				
Pentoxone		C			
Pentyl Penta-noate	A				
Peracetic Acid	C				
Perchloric Acid - 2N	A	A	A	A	A
Perchloroethy-lene	A	A	A	C	A
Perfluoropropane					
Perfluorotriethyl-amine					
Permanganic Acid					
Persulfuric Acid (Caro's Acid)					
Petrolatum	A	A	A		A
Petrolatum Ether	A	A			
Petroleum Oil, Above 250°F	B	A	A		
Petroleum Oil, Below 250°F	A	A	A		
Petroleum Oil, Crude	A	A	A		
Phenol	A	A	A	A	A
Phenol, 70% / 30% H2O	A	A	A	A	A
Phenol, 85% / 15% H2O	A	A	A	A	A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Phenolic Sulfo-nate	C				
Phenolsulfonic Acid	C	A	A		
Phenylacetamide	A				
Phenylacetate	C	B	A		
Phenylacetic Acid	C				
Phenylbenzene	A	A	A		
Phenylene Dia-mine		C			
Phenylethyl Alcohol	A				
Phenylethyl Ether	D	B	A		
Phenylethyl Malonic Ester*	A				
Phenylglycerine	C				
Phenylhydrazine	A	B	A		
Phenylhydrazine Hydrochloride	C				
Phenylmercuric Acetate	C	C			
Phorone	D	C	A		
Phosgene		D	A		
Phosphine					
Phosphoric Acid 3 Molar to 158°F	A	A	A	B	
Phosphoric Acid Concentrated Room Temp	A	A	A	B	C
Phosphoric Acid Concentrated to 158°F	A	A	A	B	C
Phosphoric Acid, 20%		A	A	B	A
Phosphoric Acid, 45%		A	A	B	B

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Phosphorus (Molten)					
Phosphorus Oxychloride			A		
Phosphorus Trichloride	A	A	A		
Phosphorus Trichloride Acid	A		A		A
Phthalic Acid	C	A		A	A
Phthalic Anhydride	C	C	A	A	B
Pickling Solution 3 2	B	A			
Picric Acid (aq)	A	A	A	D	A
Picric Acid Molten	A				
Pine Oil	A	A	A		A
Pine Tar	A	A			
Pinene	A	A	A		
Piperazine	A				
Piperidine	A		A		
Piranha (H ₂ SO ₄ :H ₂ O ₂) (70:30)					
Plating Solution (Co,Cu,Au,In,Fe,Pb,Ni,Ag,Sn,Zn)	A	A			A
Plating Solutions Chrome	A	A	A		A
Plating Solutions Others	A	A			A
Pneumatic Service	A		A		
Polyethylene Glycol	C	A			
Polyglycerol	C				
Polyglycol	C				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Polyvinyl Acetate Emulsion					B
Potassium (Molten)					
Potassium Acetate	D	C	A		
Potassium Acid Sulfate	C				
Potassium Alum	C				
Potassium Aluminum Sulfate	C				A
Potassium Antimonate	C				
Potassium Bicarbonate	C	A	A		A
Potassium Bichromate	C				A
Potassium Bifluoride	C				
Potassium Bisulfate	C	A	A		A
Potassium Bisulfite	C	A	A		
Potassium Bitartrate	C				
Potassium Bromide	C	A	A		A
Potassium Carbonate	C	A	A		A
Potassium Chlorate	C	A	A		A
Potassium Chloride	A	A	A		A
Potassium Chromates	C	A	A		B
Potassium Citrate	C				
Potassium Cupro Cyanide	A				A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Potassium Cyanate	C		A		B
Potassium Cyanide	A	A			
Potassium Dichromate	A	A	A		A
Potassium Diphosphate	C				
Potassium Ferricyanide	C	A	A		
Potassium Fluoride	C	A	A		
Potassium Gluconate	C				
Potassium Hydroxide 50%	D	A	A		B
Potassium Hypochlorite	C	B	A		
Potassium Iodate	C		A		
Potassium Iodide	C	A	A		
Potassium Metabisulfate	C				
Potassium Metachromate	C				
Potassium Metasilicate					
Potassium Monochromate	C				
Potassium Nitrate	A	A	A		B
Potassium Nitrite	C		A		
Potassium Oxalate	C		A		
Potassium Perchlorate	C	A	A		
Potassium Perfluoro Acetate					
Potassium Permanganate	C	A	A		B

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Potassium Peroxide					
Potassium Persulfate	C		A		
Potassium Phosphate (Acid)	C		A		
Potassium Phosphate (Alkaline)	C				
Potassium Phosphate (Di/Tri Basic)	C				
Potassium Pyrosulfate	C				
Potassium Salts	A		A		
Potassium Silicate		A	A		
Potassium Sodium Tartrate	C				
Potassium Stannate	C				
Potassium Stearate	C	A			
Potassium Sulfate	A	A	A		B
Potassium Sulfide	C	A	A		B
Potassium Sulfite	A	A	A		A
Potassium Tartrate	C		A		
Potassium Thiocyanate	C		A		
Potassium Thiosulfate	C				
Potassium Triphosphate	C				A
Prestone Anti-freeze	A	A			
PRL-High Temp. Hydr. Oil	A	A			
Producer Gas	A	A	A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Propane	A	A	A	A	A
Propanol			A		
Propionaldehyde	C	C	A		
Propionic Acid	C	B	A		A
Propionitrile	A	C	A		
Propyl Acetate	D	C	A		A
Propyl Acetone or n-Propyl Acetone	D	B			
Propyl Alcohol	A	A	A		A
Propyl Nitrate	D		A		
Propyl Propionate	C				
Propylamine	C	C			
Propylbenzene	A	A			
Propylene	A	A	A		
Propylene Chloride	A	A	A		
Propylene Chlorohydrin	A				
Propylene Dichloride	A	A	A		
Propylene Glycol	C	A	A	A	A
Propylene Imine	A				
Propylene Oxide	D	D	A	A	A
Pydraul 90e	A	A			
Pydraul, 10E	D	A			
Pydraul, 115E	A	A			
Pydraul, 230C, 312C, 540C, A200	A	A			
Pydraul, 29ELT 30E, 50E, 65E	A	A			
Pyranol Transformer Oil	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Pyridine	A	A	A	C	B
Pyridine Oil	D	C			
Pyridine Sulfate	C				
Pyridine Sulfonic Acid	C				
Pyrogallol (Pyrogallic Acid)	A		A		A
Pyrogard 42, 43, 55	A	A			
Pyrogard 53, Mobil Phosphate Ester	A	A			
Pyrogard D, Mobil Water-in-Oil Emulsion	D	A			
Pyroligneous Acid	D	C			
Pyrolube	A	A			
Pyrosulfuric Acid	C				
Pyrosulfuryl Chloride	A				
Pyrrole	D	B	A		
Pyruvic Acid	C				
Quinidine	A				
Quinine	A	A	A		
Quinine Bisulfate	C				
Quinine Hydrochloride	C				
Quinine Sulfate	C				
Quinine Tartrate	C				
Quinizarin	A	A			
Quinoline	A	A			
Quinone	A	A	A		A
Radiation (Gamma, 1.0 E +07 Rads)	D	C			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Raffinate	A	A			
Rapeseed Oil	A	A	A		
Red Line 100 Oil	A	A			
Red Oil (MIL-H-5606)	A	A	A		
Resorcinol	C	A			
Rhodium					
Riboflavin	A	A			
Ricinoleic Acid	A	A			
RJ-1 (MIL-F-25558)	A	A	A		
RJ-4 (MIL-F-82522)	A	A			
Rosin	A	A	A		A
RP-1 (MIL-R-25576)	A	A			
Saccharin Solution	C				
Sal Ammoniac	A	A	A		
Salicylic Acid	A	A	A	A	A
Santo Safe 300	A	A			
Sea (Salt) Water	A	A	A		C
Sebacic Acid	C	A			
Selenic Acid	C				
Selenous Acid	C				
Sewage	A	A	A		
SF 1154 GE Silicone Fluid	A	A			
SF1147 GE Silicone Fluid	A	A			
SF96 GE Silicone Fluid	A	A			
Shell 3XF Mine Fluid (Fire resist hydr.)	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Shell Alvania Grease #2	A	A			
Shell Carnea 19 and 29	A	A			
Shell Diala	A	A			
Shell Irus 905	A	AA			
Shell Lo Hydrax 27 and 29	A	A			
Shell Macome 72	A	A			
Shell Tellus #32 (Petroleum Base)	A	A			
Shell Tellus #68	A	A			
Shell Tellus 27 (Petroleum Base)	A	A			
Shell Tellus 33	A	A			
Shell UMF (5% Aromatic)	A	A			
Shellac	C	A			
Silane					
Silicate Esters	A	A	A		
Silicon Fluoride					
Silicon Tetra-chloride			B		
Silicon Tetra-fluoride					
Silicone Greases	A	A	A		
Silicone Oils	A	A	A	C	A
Silver Bromide	C		A		
Silver Chloride	C		A		C
Silver Cyanide	C	A	A		A
Silver Nitrate	A	A	A	A	A
Silver Sulfate	C	A			
Sinclair Opaline CX-EP Lube	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Skelly, Solvent B, C, E	A				
Skydrol 500 B4	D	C	A	D	
Skydrol 7000	B	A	A		
Skydrol LD-4	D	C			
Soap Solutions	A	A		A	A
Socony Mobile Type A	A	A			
Socony Vacuum AMV AC781 (Grease)	A	A			
Socony Vacuum PD959B	A	A			
Soda Ash	A	A			A
Sodium (Molten)		D			
Sodium Acetate	D	A	A	A	A
Sodium Acid Bisulfate	C				
Sodium Acid Fluoride	C				
Sodium Acid Sulfate	C				
Sodium Aluminate	C	A	A		A
Sodium Aluminate Sulfate	C				
Sodium Anthraquinone Disulfate	C				
Sodium Antimonate	C				
Sodium Arsenate	C	A			
Sodium Arsenite	C		A		
Sodium Benzoate	C	A		A	
Sodium Bicarbonate (Baking Soda)	A	A	A	A	A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Sodium Bichromate	C		A		A
Sodium Bifluoride	C				
Sodium Bisulfate or Bisulfite	A	A	A		A
Sodium Bisulfide	C				
Sodium Bitartrate	C				
Sodium Borate	A	A	A		A
Sodium Bromate	C		A		
Sodium Bromide	C	A	A		A
Sodium Carbonate (Soda Ash)	A	A	A	A	B
Sodium Chlorate	C	A	A	A	A
Sodium Chloride	A	A	A	A	C
Sodium Chlorite	C		A		
Sodium Chloroacetate	C	B			
Sodium Chromate	C	A	A		A
Sodium Citrate	C		A		
Sodium Cyanamide	C				
Sodium Cyanate	C				
Sodium Cyanide		A	A	A	A
Sodium Diacetate	C	B			
Sodium Diphenyl Sulfonate	C				
Sodium Diphosphate	C				
Sodium Disilicate	C				
Sodium Ethylate	C		A		
Sodium Ferricyanide	C	A	A		A
Sodium Fluoride	C	A	A	A	A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Sodium Fluorosilicate	C				
Sodium Glutamate	C				
Sodium Hydride					
Sodium Hydrogen Sulfate	C		A		
Sodium Hydrosulfide	C	A			
Sodium Hydrosulfite	C		A		
Sodium Hydroxide, 3 Molar	B	A	A	A	B
Sodium Hypochlorite	A	A	A	A	A
Sodium Hypophosphate	C				
Sodium Hypophosphite	C				
Sodium Hyposulfite	C		A		A
Sodium Iodide	C	A	A		
Sodium Lactate	C		A		
Sodium Metaphosphate	A	A	A		A
Sodium Metasilicate	C	A	A		A
Sodium Methylate	C				
Sodium Monophosphate	C				
Sodium Nitrate		A	A	A	A
Sodium Oleate	C		A		
Sodium Orthosilicate	C				
Sodium Oxalate	C		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Sodium Perborate	A	A	A		C
Sodium Percarbonate	C				
Sodium Perchlorate	C		A		
Sodium Peroxide	A	A	A		A
Sodium Persulfate	C		A		
Sodium Phenolate	C				
Sodium Phenoxide	C				
Sodium Phosphate (Dibasic)	A	A	A		A
Sodium Phosphate (Mono)	A	A	A		A
Sodium Phosphate (Tribasic)	A	A	A		A
Sodium Plumbite	C				
Sodium Pyrophosphate	C		A		
Sodium Resinate	C				
Sodium Salicylate	C				
Sodium Salts	A	A	A	A	
Sodium Sesquioxide	X	A			
Sodium Silicate	A	A	A		B
Sodium Silicofluoride					
Sodium Stannate	C				
Sodium Sulfate	A	A	A	A	A
Sodium Sulfide and Sulfite	A	A	A	A	B
Sodium Sulfo cyanide	C				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Sodium Tartrate	C		A		
Sodium Tetraborate	C		A		A
Sodium Tetraphosphate	C				
Sodium Tetrasulfide	C				
Sodium Thioarsenate	C				
Sodium Thiocyanate	C	A			
Sodium Thiosulfate	A	A	A		A
Sodium Trichloroacetate	C				
Sodium Triphosphate	C				
Solvesso 100, 150		A			
Sorbitol	C	A			
Sour Crude Oil	A	B	B		A
Sour Natural Gas	A	B	A		
Sovasol No. 1, 2, and 3	A				
Sovasol No. 73 and 74	A				
Soybean Oil	A	A	A		A
Spry	A				
SR-10 Fuel	A	A			
SR-6 Fuel	A	A			
Standard Oil Mobilube GX90-EP Lube	A				
Stannic Ammonium Chloride	C				
Stannic Chloride	A	A	A		D

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Stannic Chloride, 50%	A		A		
Stannic Tetra-chloride	C				
Stannous Bisul-fate	C				
Stannous Bro-mide	C				
Stannous Chloride (15%)	A	A			C
Stannous Fluo-ride	C	A			
Stannous Sulfate	C				
Stauffer 7700	A	A	A		
Steam Below 400°F	D	A	A		A
Steam, 400° - 500°F	D	C	A		A
Steam, Above 500°F		C	B		A
Stearic Acid		A	A	C	A
Stoddard Solvent	A	A	A		A
Strontium Ace-tate	C	C			
Strontium Carbo-nate	C				
Strontium Chloride	C				
Strontium Hydroxide	C				
Strontium Nitrate	C				
Styrene (Mon-omer)	B	A	A	D	A
Succinic Acid	C	A	A		A
Sucrose Solutions	A	A	A		
Sulfamic Acid	C	A	A		A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Sulfanilic Acid	C				
Sulfanilic Chloride	A				
Sulfanilimide	A				
Sulfite Liquors	C	A			A
Sulfolane	B	A			
Sulfonated Oils	A				
Sulfonic Acid	C				
Sulfonyl Chloride	C				
Sulfur	A		A		A
Sulfur (Molten)	A	A			
Sulfur Chloride	A	A	A	D	D
Sulfur Dioxide, Dry	D	A	A		A
Sulfur Dioxide, Liquidified under pressure	D	A	A		A
Sulfur Dioxide, Wet	D	A	A		A
Sulfur Hexa-fluoride	C	A	B		
Sulfur Liquors	C				C
Sulfur Mono-chloride	A				
Sulfur Tetra-fluoride		A			
Sulfur Trioxide Dry	A	A	A		C
Sulfuric Acid (20% Oleum)	C	A	A		C
Sulfuric Acid, 3 Molar to 158°F	A	A	A		D
Sulfuric Acid, Concentrated Room Temp	A	A	A		D

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Sulfuric Acid, Concentrated to 158°F	A	A	A		D
Sulfuric Chlorohydrin (Chlorosulfonic Acid)	C	B			
Sulfurous Acid	A	B	A	A	B
Sunoco #3661	A	A			
Sunoco All purpose grease	A	A			
Sunoco SAE 10	A	A			
Sunsafe (Fire resist. hydr. fluid)	A	A			
Super Shell Gas	A	A			
Surfuryl Chloride	C				
Swan Finch EP Lube	A	A			
Swan Finch Hypoid-90	A				
Tallow	A	A			A
Tannic Acid (10%)	A	A	A		A
Tar, bituminous	A	A	A		A
Tartaric Acid	A	A	A	A	B
Tellone II					
Terephthalic Acid	C	A			
Terpineol	A	A	A		
Terpinyl Acetate	B	B			
Tertiary Amyl Methyl Ether (TAME)					
Tertiary Butyl Catechol or p-tert-butylcatechol	A		A		
Tertiary Butyl Mercaptan	A		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Tetrabromoethane	A	A	A		
Tetrabromomethane	A	A	A		
Tetrabutyl Titanate	A	A	A		
Tetrachloroethylene	A	A	A		
Tetrachloroethane	A	A	A		A
Tetraethyl Lead	A	A	A		
Tetraethyl Lead "Blend" V1164-75	A				
Tetraethyl Orthosilicate (TEOS)					
Tetrahydrofuran	D	B	A	D	A
Tetralin	A	A	A		
Tetramethyl Ammonium Hydroxide	C				
Tetramethylcyclotetrasiloxane (TMCTS)					
Tetramethyldihydropyridine	A				
Tetramethyldihydropyridine	A				
Tetraphosphogluconate	C				
Tetraphosphoric Acid					
Texaco 3450 Gear Oil	A	A			
Texaco Capella A and AA	A	A			
Texaco Meropa 220 (No Lead)	A	A			
Texaco Regal B	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Texaco Uni-Temp Grease	A	A			
Texamatic "A" 1581 Fluid	A	A			
Texamatic "A" 3401 Fluid	A	A			
Texamatic "A" 3525 Fluid	A	A			
Texamatic "A" 3528 Fluid	A	A			
Texamatic "A" Transmission Oil	A	A			
Texas 1500 Oil	A	A			
Therminol 44	A	A			
Therminol 55	A				
Therminol 66					
Therminol FR					
Therminol VP-1, 60, 65	A				
Thio Acid Chloride					
Thioamyl Alcohol	A				
Thiodiacetic Acid	C				
Thioethanol	C				
Thioglycolic Acid	C		A		
Thiokol TP-90B	A	A			
Thiokol TP-95	A	A			
Thionyl Chloride	A	A	A	A	
Thiophene (Thiofuran)	C	C	A		
Thiophosphoryl Chloride	C				
Thiourea	C				
Thorium Nitrate	C				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Tidewater Multi-gear, 140 EP Lube	A				
Tidewater Oil-Beedol	A				
Tin Ammonium Chloride	C				
Tin Chloride	A			A	
Tin Tetrachloride	A			A	
Titanic Acid	C				
Titanium Dioxide	C	A			
Titanium Sulfate	C		A		
Titanium Tetrachloride	A	A	B		C
Toluene	A	A	A		A
Toluene Bisodium Sulfite					
Toluene Diisocyanate (TDI)	D	C			
Toluene Sulfonyl Chloride	A				
Toluenesulfonic Acid	C				
Toluidine	A	B	A		
Toluol	C	C	A	D	A
Toluquinone	A				
Tolylaldehyde	C				
Transformer Oil	A	A	A		A
Transmission Fluid Type A	A	A	A		
Triacetin	D	B	A		
Triaryl Phosphate	A				
Tribromomethylbenzene	A				
Tributoxyethyl Phosphate	A		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Tributyl Citrate	C	C			
Tributyl Mercaptan	A	A	A		
Tributyl Phosphate	D	C	A		A
Tributylamine					
Trichloroacetic Acid	C	B	A	B	B
Trichloroacetyl Chloride	A				
Trichlorobenzene	A	A	A		
Trichloroethane	A	A	A	C	A
Trichloroethanolamine	C				
Trichloroethylene	A	A	A	C	A
Trichloromethane	A				
Trichloronitromethane (Chloropicrin)	C				
Trichlorophenylsilane					
Trichloropropane	A	A	A	C	A
Trichlorosilane	A				
Tricresyl Phosphate	B	A		A	A
Triethanol Amine	D	C		C	A
Triethyl Phosphate	A				
Triethylaluminum		A			
Triethylborane		A	A		
Triethylene Glycol	C	A			
Triethylenetetramine	C	C			
Trifluoroacetic Acid	C		A		

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Trifluoroethane	A		A		
Trifluoromethane	A				
Trifluorovinylchloride	A				
Triisopropylbenzylchloride	A				
Trimethylamine	C	C			
Trimethylamine (TMA)	C				
Trimethylbenzene	A				
Trimethylborate (TMB)	A				
Trimethylpentane	A	A	A		
Trinitrololuene (TNT)	B	A	A		
Trioctyl Phosphate	B	A	A		
Triphenylphosphate	C		A		
Tripoly Phosphate	B		A		
Tripotassium Phosphate	C				
Trisodium Phosphate	C				A
Tritium					
Tung Oil (China Wood Oil)	A	A			
Tungsten Hexafluoride					
Tungstic Acid					
Turbine Oil	A	A	A		
Turbine Oil #15 (MIL-L-7808A)	A	A			
Turbo Oil #35	A	A			
Turpentine	A	A	A	D	A

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Type I Fuel (MIL-S-3136)(ASTM Ref. Fuel A)	A	A	A		
Type II Fuel MIL-S-3136	A	A	A		
Type III Fuel MIL-S-3136(ASTM Ref. Fuel B)	A	A	A		
Ucon Hydrolube J-4	A	A			
Ucon Lubricant 50-HB-100	A	A			
Ucon Lubricant 50-HB-260	A	A			
Ucon Lubricant 50-HB-5100	A	A			
Ucon Lubricant 50-HB55	A	A			
Ucon Lubricant 50-HB-660	A	A			
Ucon Lubricant LB-1145	A	A			
Ucon Lubricant LB-135	A	A			
Ucon Lubricant LB-285	A	A			
Ucon Lubricant LB-300X	A	A			
Ucon Lubricant LB-625	A	A			
Ucon Lubricant LB-65	A	A			
Ucon Oil 50-HB-280X	C	C			
Ucon Oil Heat Transfer Fluid 500 (Polyalkalene Glycol)	A	A			
Ucon Oil LB-385	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Ucon Oil LB-400X	A	A			
Undecylenic Acid	A				
Undecylic Acid	A				
Univis 40 (Hydr. Fluid)	A	A			
Univolt #35 (Mineral Oil)	A	A			
Unsymmetrical Dimethyl Hydrazine (UDMH)	D		B		
UPDI(Ultrapure Deionized Water)	C				
Uranium Hexachloride	A				
Uranium Hexafluoride					
Uranium Sulfate Factory					
Uric Acid	C		A	A	
Valeraldehyde	C	C			
Valeric Acid	C	A	A		
Vanadium Oxide	A				
Vanadium Pentoxide	A				
Varnish	A	A	A		A
Vegetable Oil	A	A	A		A
Versilube F44, F55	A	A			
Versilube F-50	A	A			
Vinegar	C	A	A	A	A
Vinyl Acetate	C	C	A	B	
Vinyl Benzene	A		A		
Vinyl Benzoate	A				
Vinyl Chloride	A	A	A		
Vinyl Fluoride	A	A			

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Vinylidene Chloride	A	A			
Vinylpyridine	A				
Vitriol (White)	C				
VV-H-910	A	A			
Wagner 21B Brake Fluid	D	B			
Water	A	A	A	A	A
Wemco C	A	A			
Whiskey and Wines	A	A	A		A
White Liquor	A	A			A
White Oil	A	A	A		A
White Pine Oil	A	A	A		
Wolmar Salt	A	A			
Wood Alcohol	D	A	A		
Wood Oil	A		A		
Xenon	A	A	A		
Xylene	A	A	A		A
Xylidenes-Mixed-Aromatic Amines	D	C	A		
Xylol	A	A		D	
Zeolites	A	A	A		
Zinc Acetate	D	B	A		A
Zinc Ammonium Chloride	C	B	A		
Zinc Chloride	A	A	A	A	B
Zinc Chromate	C	B			
Zinc Cyanide	C	B			
Zinc Diethylthiocarbamate	C	B			
Zinc Dihydrogen Phosphate	C				

List of chemical resistance

Fluid	FKM / FPM / Viton	Viton® Extreme ETP-S	FFKM / Kalrez®	TPE (LEZ-SAN Santoprene®)	Stainless Steel AISI 316L
Zinc Fluorosilicate					
Zinc Hydrosulfite	C	B	A		A
Zinc Naphthenate					
Zinc Nitrate	A	A	A		A
Zinc Oxide	A	A			
Zinc Phenolsulfonate	C	B			
Zinc Phosphate	A	A	A		
Zinc Salts	A	A	A	A	
Zinc Silicofluoride					
Zinc Stearate	C	A			
Zinc Sulfate	A	A	A		A
Zinc Sulfide	C	B			
Zirconium Nitrate	A	A			

3.4 Table 2

Fluid Source: holland® APPLIED TECHNOLOGIES www.hollandapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Acetaldehyde	B	D	A	A
Acetate LMW	—	—	A	A
Acetic acid <5%	A	—	A	B
Acetic acid >5%	A	B	A	B
Acetic anhydride	C	D	A	B
Acetone	C	D	A	A
Acetonitrile	—	D	A	A
Acetyl bromide	—	—	A	—
Acetyl chloride	C	A	A	A
Air	A	A	A*	A

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLOGIES www.hollandapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Aliphatic hydrocarbons	—	—	—	B
Aluminum chloride	B	A	A	D
Aluminum sulfate	A	A	A	B
Alums	A	A	A	—
Ammonia, gas / liquid	C	D	A	B
Ammonium acetate	—	D	A	B
Ammonium carbonate	C	A	A	B
Ammonium chloride	C	A	A	C
Ammonium hydroxide	A	B	A	A
Ammonium nitrate	C	A	A	A
Ammonium phosphate	A	A	A	B
Ammonium sulfate	A	A	A	B
Amyl acetate	D	D	A	A
Amyl alcohol	D	A	A	A
Amyl chloride	D	A	A	A
Aniline	D	B	A	A
Aniline hydrochloride	D	B	A	D
Aqua regia (80 % HCl, 20 % H)	D	B	A	D
Aromatic hydrocarbons	—	A	—	B
Arsenic salts	—	D	—	—
Barium salts	A	A	A	B
Benzaldehyde	B	D	A	B
Benzenesulfonic acid	D	A	A	B
Bleaching liquors	B	A	A	—
Boric acid	A	A	A	B

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLOGIES www.hollandapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Bromine	D	A	A	D
Butane	D	A	A	A
Butanol (butyl alcohol)	B	A	A	A
Butyl acetate	D	D	A	B
Butyric acid	D	B	A	B
Calcium oxide	A	A	A	A
Calcium salts	B	A	A	B
Carbon bisulfide	D	—	A	A
Carbon dioxide	B	A	A*	A
Carbon tetrachloride	D	A	A	B
Chlorine, dry	D	A	A*	A
Chlorine, wet	D	B	A	C
Chloroacetic acid	—	D	A	B
Chlorobenzene	D	A	B	A
Chlorobromomethane	D	A	A	—
Chloroform	D	A	A	A
Chlorosulfonic acid	D	D	A	D
Chromic acid, 30 %	C	A	A	B
Chromium salts	—	—	—	—
Copper salts	A	A	A	B
Cresol	D	A	A	A
Cyclohexane	D	A	A	A
Cyclohexanone	D	D	A	A
Diacetone alcohol	B	D	A	B
Dimethyl formamide	B	D	A	A
Essential oils	C	—	—	—
Ethanol (ethyl alcohol)	A	A	A	A

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLOGIES www.hollandapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Ether	D	D	A	A
Ethyl acetate	B	D	A	B
Ethyl bromide	D	A	A	—
Ethyl chloride	D	A	A	A
Ethylamine	C	D	—	—
Ethylene chlorohydrin	C	A	A	B
Ethylene dichloride	D	A	A	B
Ethylene glycol	A	A	A	B
Ethylene oxide	D	D	A	B
Fatty acids	C	A	A	B
Ferric chloride	B	A	A	D
Ferric sulfate	B	A	A	B
Ferrous chloride	C	A	A	D
Ferrous sulfate	C	A	A	B
Fluoboric acid	A	—	A	B
Fluoroborate salts	—	—	—	—
Fluosilicic acid	D	A	A	C
Formaldehyde	B	D	A	C
Formic acid, 25 %	B	D	A	B
Freon® TMS	—	—	A	—
Gasoline, high-aromatic	D	A	B	A
Gasoline, nonaromatic	D	A	A	—
Glucose	A	A	A	A
Glue, P.V.A.	A	A	A	A
Glycerin	A	A	A	A
Hydriodic acid	—	A	—	—

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLO- GIES www.hollan- dapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Hydrobromic acid, 30 %	D	A	A	D
Hydrochloric acid (dil)	D	A	A	D
Hydrochloric acid (med)	D	A	A	D
Hydrochloric acid (conc)	D	A	A	D
Hydrocyanic acid	C	A	A	B
Hydrocyanic acid, gas, 10 %	C	A	A	—
Hydrofluoric acid, 50 %	D	D	A	D
Hydrofluoric acid, 75 %	D	D	A	D
Hydrogen peroxide (dil)	A	A	A	B
Hydrogen peroxide, 90 %	B	A	A	B
Hypochlorous acid	D	A	A	—
Iodine solutions	C	A	A	D
Iodoform	—	C	—	A
Kerosene	D	A	A	A
Ketones	—	—	A	A
Lacquer solvents	D	D	A	A
Lactic acid, 3-10%	A	A	A	B
Lead acetate	D	D	A	B
Linseed oil	A	A	A	A
Lithium hydroxide	D	C	A	B
Magnesium chloride	A	A	A	B
Magnesium sulfate	A	A	A	B
Malic acid	B	A	A	A
Manganese salts	B	A	A	D

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLOGIES www.hollandapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Mercury salts	—	A	A	B
Methane	D	A	A*	A
Methanol (methyl alcohol)	A	B	A	A
Methyl chloride	D	B	A	A
Methyl ethyl ketone (MEK)	D	D	A	A
Mixed acid (40% H ₂ SO ₄ , 15 % HNO ₃)	—	—	A	B
Molybdenum disulfide	—	A	—	—
Monoethanolamine	B	D	A	A
N-Methyl-2-Pyrrolidone (NMP) ¹	A	C	A	—
Naphtha	D	A	B	A
Natural gas	A	A	A*	A
Nickel salts	A	A	A	B
Nitric acid (dil)	B	B	A	A
Nitric acid (med)	C	A	A	A
Nitric acid (conc)	D	A	A	A
Nitrobenzene	D	B	A	B
Nitrogen oxides	D	D	A	—
Nitrous acid	—	—	A	B
Oils, animal	B	A	A	A
Oils, mineral	B	A	A	A
Oils, vegetable	B	A	A	A
Oleic acid	D	B	A	B
Oxalic acid, cold	B	A	A	B
Oxygen, gas	B	B	A*	A
Palmitic acid, 100 % in ether	D	A	A	B

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLO- GIES www.hollan- dapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Perchloric acid	D	A	A	C
Perchloroethylene	D	A	A	B
Phenol (carbolic acid)	D	A	A	B
Phosphoric acid, 50 %	C	A	A	A
Phthalic acid	B	B	A	B
Plating solutions	D	A	A	—
Polyglycol	A	A	—	—
Potassium carbonate	—	A	—	B
Potassium chlorate	B	A	A	B
Potassium hydroxide (med)	B	D	A	B
Potassium hydroxide (conc)	C	D	A	B
Potassium iodide	—	A	A	A
Propanol (propyl alcohol)	A	A	A	A
Pyridine	D	D	A	A
Silicone fluids	C	A	A	A
Silicone oils	C	A	A	A
Silver nitrate	A	A	A	B
Soap solutions	A	A	A	A
Sodium bicarbonate	A	A	A	B
Sodium bisulfate	—	A	A	D
Sodium bisulfite	A	A	A	B
Sodium borate	A	A	A	B
Sodium carbonate	A	A	A	A
Sodium chlorate	C	A	A	B
Sodium chloride	A	A	A	C
Sodium ferrocyanide	—	A	A	B
Sodium hydrosulfite	—	—	A	—

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLOGIES www.hollandapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Sodium hydroxide (dil)	A	A	A	A
Sodium hydroxide, 25 %	B	A	A	B
Sodium hydroxide (conc)	—	A	A	C
Sodium hypochlorite, <5%	B	A	A	A
Sodium hypochlorite, >5%	B	A	A	C
Sodium nitrate	D	A	A	B
Sodium silicate	A	A	A	B
Sodium sulfide	A	A	A	C
Sodium sulfite	A	A	A	A
Steam, up to 40 psi	A	B	A*	A
Stearic acid	B	A	A	B
Styrene	D	A	A	A
Sulfuric acid (dil)	D	A	A	D
Sulfuric acid (med)	D	A	A	D
Sulfuric acid (conc)	D	A	A	C
Sulfurous acid	D	B	A	B
Tannic acid	B	A	A	B
Tanning liquors	—	—	A	A
Tartaric acid	A	A	A	C
Tin salts	B	—	A	—
Toluene (toluol)	D	A	A	A
Trichloroacetic acid	D	C	A	D
Trichloroethylene	D	A	A	B
Trisodium phosphate	—	A	A	B
Turpentine	D	A	A	A
Urea	B	—	A	A

List of chemical resistance

Fluid Source: holland® APPLIED TECHNOLOGIES www.hollandapt.com	Silicone (peroxide/ platinum- cured)	Viton®	PTFE (Teflon)	Stainless steel
Uric acid	—	—	A	B
Water, fresh	B	A	A	A
Water, salt	A	A	A	B
Xylene	D	A	A	A
Zinc chloride	A	A	A	D

¹ see: <https://www.lyondellbasell.com/globalassets/documents/chemicals-technical-literature/elastomer-compatibility-2688>

3.5 Table 3

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Abietic acid				A
Acetaldehyde (ethanal), 40%	A	A	A	
Acetamide	A	A	A	C
Acetamide, 50%	A			
Acetic acid (glacial acetic acid), concentrated	C	A	A	C
Acetic acid allyl ester (allyl acetate)		A	A	
Acetic acid anhydride (acetic anhydride)		A	A	C
Acetic acid butyl ester (butyl acetate)	A	A	A	C
Acetic acid chloride (acetyl chloride)		A	A	
Acetic acid ethyl ester (ethyl acetate)	C	A	A	C
Acetic acid methyl ester (methyl acetate)	C	A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Acetic acid vinyl ester (vinyl acetate)		A	A	
Acetic acid, 50%	C	A	A	
Acetic acid, 10%	A	A	A	
Acetic acid, 5%	A	A	A	a
Acetic acid, 90%		A	A	
Acetic anhydride (acetic acid anhydride)		A	A	C
Acetic ester (ethyl acetate, acetic acid ethyl ester)	C	A	A	C
Acetoacetic ester			A	C
Acetone (dimethyl ketone, propanone)	C	A	A	A
Acetonitrile (methyl cyanide)		A	A	
Acetophenone	A	A	A	
Acetyl cellulose (cellulose acetate)	A	A	A	A
Acetyl chloride (acetic acid chloride)		A	A	
Acetylacetone	A	A	A	
Acetylene gas	A	A	A	C
Acetylene tetrabromide (tetrabromoethane)		A	A	
Acetylene tetrachloride (tetrachloroethane)	A	A	A	
Acetylsalicylic acid		A	A	
Acrylic acid		A	A	
Acrylic acid ethyl ester (ethyl acrylate)	A	A	A	
Acrylonitrile		A	A	
Adipic acid	A	A	A	A
Adipic acid, aqueous	A	A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Aero HFA Mobil			A	
Aero Lubriplate			A	C
Aero Safe 2300			A	
Aero Safe 2300 W			A	
Aero Shell 17 Lubricants			A	C
Aero Shell 750			A	
Aero Shell 7A Lubricants			A	C
Aero Shell Fluid 4 (41), +20 °C			A	
Aero Shell IAC			A	C
Aerozene 50 (50% Hydrazine, 50% UDMH)			A	
Aircraft engine fuels (JP)	A		A	
Alanine		A	A	
Alcohol	A	A	A	C
Alkazene (dibromoethylbenzene)			A	
Allyl acetate (acetic acid allyl ester)		A	A	
Allyl alcohol	A	A	A	A
Allyl alcohol (2-propen-1-ol)	C	A	A	
Allyl chloride (3-chloro-1-propene)		A	A	A
Almond oil			A	
Alum (aluminum potassium sulfate), aqueous	A	A	A	C
Aluminum acetate, aqueous	A	A	A	
Aluminum ammonium sulfate	C	A	A	
Aluminum bromide			A	A
Aluminum chloride	A	A	A	C
Aluminum fluoride	C	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Aluminum hydroxide	A	A	A	A
Aluminum nitrate	C	A	A	C
Aluminum oxide	A	A	A	A
Aluminum phosphate, aqueous	A	A	A	A
Aluminum potassium sul- fate (alum), aqueous	A	A	A	C
Aluminum potassium sul- fate, diluted	C	A	A	
Aluminum potassium sul- fate, saturated	C	A	A	
Aluminum sulfate	C	A	A	A
Aluminum sulfate, saturated	C	A	A	
Ambrex 33 (Mobil)			A	
Ambrex 830 (Mobil)			A	C
Amino acids	A	A	A	A
Aminoacetic acid	A	A	A	
Aminobenzene (aniline)	C	A	A	C
Ammonia solution	A	A	A	C
Ammonia, 10%	A			
Ammonia, aqueous (ammonia solution)	A	A	A	C
Ammonia, gaseous, cold			A	A
Ammonia, gaseous, hot				A
Ammonia, liquid (anhy- drous)		A	A	A
Ammonium acetate	A	A	A	
Ammonium carbonate (sal volatile)	A	A	A	
Ammonium carbonate, 50%		A	A	
Ammonium carbonate, aqueous		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Ammonium chloride (sal-miac)	C	A	A	A
Ammonium chloride, 2-molar			A	
Ammonium chloride, aqueous	A	A	A	
Ammonium chloride, solid	A		A	
Ammonium dihydrogen phosphate		A	A	
Ammonium fluoride (Fluorrammon)	A	A	A	A
Ammonium fluoride (Fluorrammon), aqueous		A	A	
Ammonium fluoride (Fluorrammon), saturated		A	A	
Ammonium glycolate		A	A	
Ammonium heptamolybdate		A	A	
Ammonium hydrogen carbonate		A	A	
Ammonium hydrogen difluoride		A	A	
Ammonium hydrogen fluoride (glass etchant)		A	A	
Ammonium hydrosulfide		A	A	
Ammonium hydroxide	A	A	A	
Ammonium hydroxide, 5%	A	A	A	
Ammonium hydroxide, 30%	C	A	A	A
Ammonium hydroxide, aqueous		A	A	C
Ammonium hydroxide, concentrated			A	A
Ammonium iron(II) sulfate		A	A	
Ammonium iron(III) sulfate		A	A	
Ammonium metaphosphate		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Ammonium nitrate (fertilizer)	A	A	A	C
Ammonium nitrate, 10%	A	A	A	
Ammonium nitrate, saturated	A	A	A	
Ammonium nitrite		A	A	C
Ammonium oxalate		A	A	
Ammonium peroxodisulfate		A	A	
Ammonium persulfate, 10%			A	
Ammonium phosphate (fertilizer)	A	A	A	C
Ammonium salts of mineral acids	A			
Ammonium sulfate (fertilizer)	A	A	A	C
Ammonium sulfate, 10%	A	A	A	
Ammonium sulfate, saturated	A	A	A	
Ammonium sulfide		A	A	C
Ammonium sulfide, aqueous		A	A	
Ammonium thiocyanate	A	A	A	
Amyl acetate (pentyl acetate)	A	A	A	
Amyl alcohol (pentanol, pentyl alcohol)	A	A	A	
Amyl borate		A	A	
Amyl chloride (pentyl chloride, 1-chloropentane)	A	A	A	
Amyl chloronaphtalene			A	
Amyl naphtalene		A	A	
AN-O-3 Grade M			A	C
AN-O-366			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
AN-O-6			A	
AN-W-O-366b Hydraulic Fluid			A	
Anderol, L 774, +20 °C (diester)			A	
Anderol, L 826, +20 °C (diester)			A	
Anderol, L 829, +20 °C (diester)			A	
Anethole		A	A	
Ang 25 (diester-based) TG 749			A	C
Ang 25 (glycerol ester)			A	C
Aniline (aminobenzene)	C	A	A	C
Aniline chlorohydrate		A	A	C
Aniline dyes			A	
Aniline hydrochloride		A	A	
Animal fats	A	A	A	C
Animal oil			A	C
Anise		A		
Anisole (methoxybenzene, methyl phenyl ether)	C	A	A	
Anone (cyclohexanone)	A	A	A	
Ansul ether 161 or 181			A	
Anthraquinonesulfonic acid, aqueous			A	
Antichlor (sodium thiosulfate, fixing salt)	C	A	A	A
Antiformin, aqueous			A	
Antifreezes (glycol-based)	A		A	A
Antimony chloride			A	
Antimony trichloride		A	A	
Antimony trichloride, 90%		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Antimony trichloride, aqueous		A		
Apple juice		A	A	
Aqua regia		A	A	
Argon gas	A	A	A	A
Aroclor, 1248			A	C
Aroclor, 1254			A	
Aroclor, 1260			A	A
Arsenic acid		A	A	A
Arsenic acid, aqueous		A	A	
Arsenic pentoxide			A	
Arsenic trichloride			A	
Ascorbic acid		A	A	
Askarels (e.g. Clophen, PCB)			A	
Asphalt			A	
ASTM Fuel A, +20 °C			A	
ASTM Fuel B, +20 °C			A	
ASTM Fuel C, +20 °C			A	
ASTM Oil No. 1, +100 °C			A	C
ASTM Oil No. 1, +20 °C				C
ASTM Oil No. 1, +70 °C			A	C
ASTM Oil No. 2, +100 °C			A	
ASTM Oil No. 2, +20 °C			A	C
ASTM Oil No. 2, +70 °C			A	
ASTM Oil No. 3, +100 °C			A	
ASTM Oil No. 3, +20 °C			A	
ASTM Oil No. 3, +70 °C			A	
ASTM Oil No. 4, +20 °C			A	
ASTM Reference Fuel A, +20 °C			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
ASTM Reference Fuel B, +20 °C			A	
ASTM Reference Fuel C, +20 °C			A	
ATE Brake fluid			A	C
ATF Oil			A	
ATL 857			A	
Atlantic Dominion F			A	
Atlantic Utro Gear-EP-Lube			A	
Atropine sulfate		A	A	
Aurex 903R (Mobil)			A	
Ball-bearing grease				C
Bardol B			A	
Barium bromide		A	A	
Barium carbonate	A	A	A	
Barium chloride	A	A	A	A
Barium chloride, aqueous		A	A	
Barium chloride, saturated		A	A	
Barium hydroxide	A	A	A	A
Barium hydroxide, aqueous		A	A	
Barium hydroxide, concentrated, +100 °C			A	
Barium hydroxide, saturated		A	A	
Barium salts of mineral acids	A			
Barium sulfate (barite, heavy spar)	A	A	A	A
Barium sulfide	A	A	A	A
Basic aluminium acetate	A	A	A	
Battery acid		A	A	
Bayol 35			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Bayol D			A	
BC 48 (cutting oil)			A	
Beef tallow	A		A	C
Beef tallow emulsion			A	
Beer	A	A	A	A
Beeswax	A	A	A	
Benzaldehyde (benzoic aldehyde)	A	A	A	
Benzaldoxime, aqueous			A	
Benzene	C	A	A	
Benzenesulfonic acid		A	A	
Benzenesulfonic acid, 10%			A	
Benzoic acid (sodium salt)	A	A	A	A
Benzoic acid benzyl ester			A	
Benzoic acid ethyl ester		A	A	
Benzoic acid methyl ester			A	
Benzoic acid, aqueous	A	A	A	
Benzoic acid, saturated	A	A	A	
Benzoic aldehyde (benzaldehyde)	A	A	A	
Benzophenone			A	
Benzoyl chloride	A		A	
Benzyl acetate		A	A	
Benzyl alcohol (phenylcarbinol)	A	A	A	C
Benzyl benzoate			A	
Benzyl carbinol (phenethyl alcohol)	A	A	A	
Benzyl chloride (d-chlorotoluene)	A	A	A	
Benzylamine	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Bismuth chloride			A	
Bismuth subnitrate			A	
Bisulfite solution			A	A
Bisulfite solution, containing SO ₂			A	
Bitter orange oil		A		
Bitumen	A	A	A	C
Black liquor			A	
Black Point 77			A	
Blast furnace gas			A	A
Bleaching powder	A	A	A	C
Bleaching powder, aqueous			A	
Blue vitriol (copper sulfate)	A	A	A	A
Bone oil		A	A	
Borax (sodium tetraborate)	A	A	A	C
Bordeaux mixture			A	A
Boric acid	A	A	A	A
Boric acid, 10%	A	A	A	A
Boric acid, aqueous	A	A	A	
Boron fluid (HEF)			A	
Brake fluid, ATE blue (glycol based)	A	A	A	A
Bray GG-130			A	
Brayco 719-R (W-H-910)				C
Brayco 885 (MIL-L-6085A)			A	
Bret 710			A	
Brindi acid			A	
Brine	A	A	A	
Bromine		A	A	
Bromine vapors		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Bromine water, saturated		A	A	
Bromine, liquid		A	A	
Bromobenzene (monobromobenzene)	A	A	A	
Bromochloromethane			A	
Bromochlorotrifluoroethane			A	
Bromoform		A	A	
Bromomethane	A	A	A	
Bromonaphthalene		A	A	
Bromotrifluoromethane	A			
Butadiene	A	A	A	
Butanal (butyraldehyde)	C	A	A	
Butane	A	A	A	
Butane 2,2-dimethyl			A	
Butane 2,3-dimethyl			A	
Butane, gaseous	A	A	A	
Butane, liquid	A	A	A	
Butanediol	A	A	A	
Butanetriol, aqueous		A	A	A
Butanoic acid (butyric acid, propanecarboxylic acid)	C	A	A	
Butanol (butyl alcohol)	A	A	A	C
Butanol (butyl alcohol), secondary		A	A	
Butanol (butyl alcohol), tertiary		A	A	
Butanol-1 (butyl alcohol)	A	A	A	A
Butanone (methyl ethyl ketone, MEK)	A	A	A	C
Butene	A	A	A	
Butinol			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Butoxyethanol (butyl cello-solve)			A	A
Butter	A	A	A	A
Butylamine	C			
Butyl acetate (acetic acid butyl ester)	A	A	A	C
Butyl acetyl ricinol			A	
Butyl acetyl ricinoleate			A	
Butyl acrylate		A	A	
Butyl alcohol (butanol)	A	A	A	C
Butyl alcohol (butanol), secondary		A	A	
Butyl alcohol (butanol), tertiary		A	A	
Butyl benzoate		A	A	
Butyl butyrate			A	
Butyl carbitol			A	
Butyl cellosolve (butoxyethanol)			A	A
Butyl ether (dibutyl ether)		A	A	C
Butyl glycol	A	A	A	
Butyl glycol adipate			A	C
Butyl glycol ether	A	A	A	
Butyl mercaptan (1-butane-thiol)		A	A	
Butyl methacrylate		A	A	
Butyl methyl ether	A	A	A	
Butyl oleate	A	A	A	
Butyl stearate			A	C
Butylamine		A	A	C
Butylcatechol			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Butylene glycol (2-butoxyethanol, butyl cellosolve)	A	A	A	A
Butylene, liquid	A	A	A	
Butylphenol		A	A	
Butylphenol, p-tertiary			A	
Butyraldehyde (butanal)	C	A	A	
Butyric acid (butanoic acid, propanecarboxylic acid)	C	A	A	
Butyric acid butyl ester			A	
Butyrolactone				C
Cadmium bromide		A	A	
Calcium acetate		A	A	
Calcium arsenate	A	A	A	
Calcium bicarbonate	A	A	A	
Calcium bisulfite	A	A	A	C
Calcium bisulfite, aqueous		A	A	
Calcium bisulfite, saturated		A	A	
Calcium bromide		A	A	
Calcium carbide			A	
Calcium carbonate (chalk)	A	A	A	A
Calcium chlorate		A		
Calcium chloride	A	A	A	C
Calcium chloride, 10%	A			
Calcium chloride, alcoholic		A	A	
Calcium chloride, aqueous	A	A	A	A
Calcium cyanide			A	A
Calcium hydroxide (milk of lime)	A	A	A	A
Calcium hydroxide (milk of lime), aqueous	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Calcium hydroxide (milk of lime), concentrated	A	A	A	A
Calcium hypochlorite	A	A	A	A
Calcium hypochlorite, aqueous	C	A	A	C
Calcium hypochlorite, saturated	A	A	A	
Calcium nitrate, 50%		A	A	
Calcium nitrate, aqueous		A	A	C
Calcium oxide		A	A	
Calcium phosphate	A	A	A	A
Calcium phosphate, aqueous	A	A	A	A
Calcium silicate			A	
Calcium sulfate (gypsum)	A	A	A	
Calcium sulfide		A	A	C
Calcium sulfide, aqueous		A	A	
Calcium sulfite			A	A
Calcium thiosulfate			A	A
Caliche solution (Chile salt-peter)	A	A	A	C
Camphor		A	A	
Camphor oil		A	A	
Camphor oil (camphor)		A	A	
Caprylic acid (octanoic acid)		A	A	
Caprylic aldehyde (hexanal)			A	C
Caraway	A			
Carbamate			A	
Carbazole		A		
Carbitol (diethylene glycol monoethyl ether)			A	C
Carbolic acid (phenol)		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Carbolineum	A		A	
Carbon dioxide	A		A	
Carbon dioxide, dry			A	C
Carbon dioxide, wet	A		A	A
Carbon disulfide	A	A	A	A
Carbon monoxide, dry	A		A	A
Carbon monoxide-con- taining waste gases			A	A
Carbon tetrachloride (tetra- chloromethane)	C	A	A	
Carbon tetrachloride (tetra- chloromethane, tetra)	C	A	A	
Carbonic acid	A	A	A	A
Carnauba wax		A	A	
Castor oil		A	A	A
Caustic potash (potassium hydroxide, potash lye)	A	A	A	A
Caustic soda (sodium hydroxide)		A	A	A
Caustic soda (sodium hydroxide, soda lye)	A	A	A	
Caustic soda (sodium hydroxide, soda lye), 50%	A	A	A	C
Cedar oil		A		
Cellosolve (acetate)			A	
Cellosolve (ethyl glycol)	A	A	A	
Cellugard			A	A
Cellulose acetate (acetyl cel- lulose)	A	A	A	A
Cellulose thinner			A	
Cellulube 90, 100, 150, 220, 300, 500			A	A
Cesium bromide		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Cetane			A	
Cetyl alcohol (1-hexadecanol)		A	A	
Chalk (calcium carbonate)	A	A	A	A
Chloral hydrate			A	
Chloral hydrate, aqueous			A	
Chloramine		A	A	
Chlorax			A	
Chlordane			A	
Chlorextol			A	
Chloric acid		A	A	
Chloric acid, 1%			A	
Chloric acid, 10%			A	
Chloric acid, 20%			A	
Chlorine dioxide		A	A	
Chlorine gas		A	A	
Chlorine gas, dry	C	A	A	
Chlorine gas, wet		A	A	
Chlorine sulfide (sulfur chloride)		A	A	
Chlorine water		A	A	
Chlorine water, saturated		A	A	
Chlorine, 10%, wet		A	A	
Chlorine, 97%		A	A	
Chlorine, gaseous, dry			A	
Chlorine, gaseous, moist			A	
Chlorine, liquid		A	A	
Chloroacetaldehyde			A	
Chloroacetic acid (ethyl chloroacetate)		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Chloroacetic acid ethyl ester (ethyl chloroacetate)		A	A	
Chloroacetone		A	A	
Chloroacetophenone, p-		A		
Chloroaniline		A	A	
Chlorobenzene (monochloro- benzene)	A	A	A	A
Chlorobromomethane (methylene chlorobromide)	C	A	A	
Chlorobutadiene (chloro- prene)		A	A	
Chlorobutane		A	A	
Chlorocarbonic acid ethyl ester			A	
Chlorodecane			A	
Chlorodifluoromethane	A	C	A	
Chlorododecane			A	
Chloroethane (ethyl chloride)	A	A	A	
Chloroethanol (chloroethyl alcohol, ethylene chlorohy- drin)	C	A	A	
Chloroethylbenzene, ortho-			A	
Chlorofluoromethane	A			
Chloroform (trichlorome- thane)		A	A	C
Chloromethane	A	A	A	
Chloromethyl		A	A	
Chloronaphthalene		A	A	
Chloropentafluoroethane	A			
Chlorophenol, ortho-			A	
Chloroprene (chlorobuta- diene)		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Chlorosulfuric acid		A	A	
Chloroethene (trichloroethane, methyl chloroform)	C	A	A	
Chlorotoluene		A	A	
Chlorotrifluoromethane	A			
Chrome alum		A	A	A
Chrome bath electrolytes			A	C
Chromic acid			A	
Chromic acid, 10%	C	A	A	C
Chromic acid, 20%		A	A	
Chromic acid, 50%		A	A	
Chromium anhydride (chromium trioxide)		A	A	
Chromium oxide, 0,88%, aqueous			A	C
Chromium oxychloride (chromyl chloride)		A	A	
Chromium salts		A	A	
Chromium trioxide (chromium anhydride)		A	A	
Chromosulfuric acid		A	A	
Chromyl chloride (chromium oxychloride)		A	A	
Cinnamaldehyde		A	A	A
Cinnamon oil		A		
Circo Light Process Oil			A	
Citric acid	C	A	A	
Citric acid, 10%	C	A	A	
Citric acid, 50%	A	A	A	
Citric acid, aqueous	C	A	A	A
Citric acid, saturated	A	A	A	
Citrus fruits, citrus juices	A			

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Citrus juices	A	A	A	
Citrus oils	A	A	A	C
City Service # 65, #120, # 250			A	
City Service Koolmotor-AP Gear Oil 140			A	
City Service Pacemaker #2			A	
Clophen (askarels)			A	
Clophen (polychlorinated biphenyl)	A	A	A	A
Clophen A			A	A
Clophen A60, 50%	A			
Cloves			A	
Coal gas	A	A	A	A
Coal gas, without benzene			A	
Coal tar oil	A			
Cobalt chloride, aqueous			A	A
Cobalt(II) chloride		A	A	
Cocoa	A	A		
Cocoa butter	A	A	A	
Coconut fatty alcohol			A	
Coconut oil		A	A	A
Coconut oil (hardened)			A	A
Cod liver oil	A	A	A	A
Coffee			A	A
Coke oven gas			A	
Colamine (ethanolamine)		A	A	C
Colza oil	A	A	A	
Common salt (sodium chloride)	A	A	A	A
Compressed air			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Compressed-air supply			A	
Cooking fats, cooking oils	A	A	A	A
Coolanol (Monsanto), silicone oil			A	
Copper acetate, aqueous		A	A	
Copper chloride, aqueous	C	A	A	A
Copper cyanide			A	A
Copper fluoride, aqueous		A	A	
Copper nitrate, aqueous	A	A	A	
Copper sulfate (blue vitriol)	A	A	A	A
Copper sulfate (blue vitriol), 10%	A		A	A
Copper(I) chloride			A	
Copper(II) chloride			A	
Copper(II) nitrate, aqueous	A		A	
Copper(II) nitrate, saturated	A		A	
Corn germ oil			A	
Corn oil		A	A	C
Cottonseed oil	A	A	A	A
Creosol (methylcatechol)			A	
Creosote (wood tar)		A	A	
Cresol		A	A	
Cresol (o-, m-, p-methylphenols)		A	A	
Cresylic acid			A	
Crotonaldehyde		A	A	
Crude oil	A	A	A	
Cumene (isopropylbenzene)	A	A	A	
Curry		A		
Cutting oil			A	
Cyclanon	A		A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Cycloaliphatic hydrocarbons	A			
Cyclohexamine			A	
Cyclohexane (hexamethylene, hexahydrobenzene)	A	A	A	C
Cyclohexanol (hexalin, anol)	A	A	A	
Cyclohexanone (anone)	A	A	A	
Cyclohexylamine		A	A	
Cyclopentane		A	A	
Cymene		A	A	
Cymene, para			A	
Decahydronaphthalene (decane)	A	A	A	
Decalin (decahydronaphthalene, decane)	A	A	A	
Decane	A	A	A	C
Decanol	A	A	A	C
Dehydroacetic acid		A	A	
Delco brake fluid			A	
Denatured alcohol			A	C
Densodrin W			A	
Desiccator fat			A	
Desmophen			A	
Developing bath (photo)			A	
Dexron ATF			A	
Dextrin	A	A	A	A
Dextrin, aqueous	A	A	A	A
Dextrorotatory d-tartaric acid	C	A	A	A
Diacetone (diacetone alcohol, pyranton)	A	A	A	A
Diacetone alcohol (pyranton, Dial, DA)	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Diazinon (insecticide)			A	
Dibenzyl ether	A	A	A	C
Dibenzyl sebacate		A	A	
Dibromodifluoromethane			A	
Dibromoethane		A	A	
Dibromoethylbenzene (alka- zene)			A	
Dibromotetrafluorome- thane	A			
Dibutyl ether (butyl ether)		A	A	C
Dibutyl phthalate (palatinol A)	A	A	A	C
Dibutyl sebacate		A	A	C
Dichloroacetic acid		A	A	
Dichloroacetic acid methyl ester		A	A	
Dichlorobenzene	A	A	A	
Dichlorobenzene, 1,2-			A	
Dichlorobenzene, 1,4-			A	
Dichlorobutane (tetra- methylene chloride)			A	
Dichlorobutylene		A	A	
Dichlorodifluoromethane	A	C	A	
Dichloroethane (ethylene chloride)	C	A	A	
Dichloroethylene (ethylene dichloride, vinylidene chloride)		A	A	
Dichlorofluoromethane	A		A	
Dichlorohexafluorocyclobu- tane	A			
Dichloroisopropyl ether		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Dichloromethane (methylene chloride)	C	A	A	C
Dichloromethylene chloride		A	A	
Dichlorotetrafluoroethane	A			
Dicothyl phthalate	A			
Dicyclohexamine		A	A	
Dicyclohexylamine			A	
Diesel fuel	A		A	
Diesel oil	A	A	A	C
Diester synthetic lubricant (MIL-L-7808)			A	
Diethanolamine (DEA)	A	A	A	
Diethyl ether (ether)	A	A	A	
Diethyl ketone (3-pentanone)	A	A	A	
Diethyl malonate		A		
Diethyl sebacate		A	A	C
Diethyl sulfate			A	
Diethylamine	A	A	A	C
Diethylbenzene		A	A	
Diethylene glycol	A	A	A	C
Diethylene glycol ether		A		
Diethylene glycol monoethyl ether (Carbitol)			A	C
Difluorochloroethane	A			
Difluoroethane	A			
Difluoromethane	A			
Difluorotetrachloroethane	A			
Diglycol (diethylene glycol)		A	A	
Diglycolic acid, 30%		A	A	
Diglycolic acid, aqueous		A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Dihydroxybenzenes (1,2-dihydroxybenzene, catechol)		A	A	
Dihydroxybenzenes (1,3-dihydroxybenzene, resorcinol)		A	A	
Dihydroxybenzenes (1,4-dihydroxybenzene, hydroquinone)		A	A	
Dihydroxysuccinic acid (tartaric acid)	C	A	A	A
Diisobutyl ketone	A	A	A	
Diisobutylene		A	A	
Diisooctyl phthalate (DOP)	A	A	A	C
Diisooctyl sebacate			A	
Diisopropyl ether (isopropyl ether)		A	A	
Diisopropyl ketone	A	A	A	
Diisopropylbenzene		A	A	
Dimethyl ether	A	A	A	
Dimethyl ketone (acetone, propanone)	C	A	A	A
Dimethyl phthalate (DMP)	A	A	A	
Dimethyl sulfoxide (DMSO)	A	A	A	A
Dimethylamine		A	A	
Dimethylaniline		A	A	C
Dimethylbenzene (xylene)	A	A	A	C
Dimethylbutane			A	
Dimethylformamide (DMF)	A	A	A	A
Dimethylhydrazine		A	A	
Dimethylpentane			A	
Dinitrogen monoxide (laughing gas)	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Dinitrotoluene			A	
Dinonyl phthalate (DNP)			A	
Diocetyl adipate			A	
Diocetyl phthalate (octal, DOP)	A	A	A	C
Diocetyl sebacate			A	
Diocetyl sebazate		A	A	
Dioxane	C	A	A	
Dioxane, 1,4-	C	A	A	
Dioxolane			A	
Dipentene			A	
Diphenyl ether (diphenyl oxide)	C	A	A	
Diphenyl oxide (diphenyl ether)	C	A	A	
Diphyl	A			
Dipropyl ketone	A			
Dipropylene glycol	A	A	A	
Dishwashing detergent	A	A	A	
Disodium phosphate	A	A	A	
Dispentene		A	A	
Disulfur dichloride (sulfur chloride)		A	A	
Dodecanol (lauryl alcohol)		A	A	
Dodecyl alcohol		A	A	
Dow Corning - 3, 4			A	
Dow Corning - 5, 11, 33, 44, 55, 200			A	
Dow Corning - 510, 551			A	
Dow Corning - 704, 705			A	
Dow Corning - 710, 1208, 4050, 6620			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Dow Corning - F60, F61, XF60			A	
Dow Guard			A	A
Downtherm A and E		A	A	
Elco 28 EP lubricant			A	C
Epichlorohydrin	A		A	
Epoxy resin			A	
Epsom salts (magnesium sulfate)	A	A	A	A
Esam 6 Fluid			A	
Essential oils			A	
Essitic, 42, 43			A	
Esso engine oil			A	
Esso Fuel 208			A	
Esso gearbox oil Type A			A	
Esso Golden Gasoline			A	
Esso Unavis No.40 (hydraulic oil)			A	
Esso WS2812 (MIL-L-7808A)			A	
Esso XP90-EP lubricant			A	
Ethanal (acetaldehyde)	A	A	A	
Ethane			A	
Ethanedioic acid (oxalic acid), aqueous		A	A	C
Ethanol (ethyl alcohol, spirit), 100%	A	A	A	C
Ethanol (ethyl alcohol, spirit), 40%	A	A	A	C
Ethanol (ethyl alcohol, spirit), 50%	A	A	A	C
Ethanol (ethyl alcohol, spirit), 96%	A	A	A	C
Ethanol, 50%	A	A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Ethanol, 96%	A	A	A	
Ethanolamine (colamine)		A	A	C
Ether (diethyl ether)	A	A	A	
Ethyl acetate (acetic acid ethyl ester, acetic ester)	C	A	A	C
Ethyl acrylate (acrylic acid ethyl ester)	A	A	A	
Ethyl alcohol	A	A	A	
Ethyl alcohol (ethanol, spirit)	A	A	A	C
Ethyl benzoate			A	
Ethyl bromide			A	
Ethyl butyrate		A		
Ethyl cellulose		A	A	
Ethyl chloride (chloroethane)	A	A	A	
Ethyl chloroacetate (chloroacetic acid ethyl ester)		A	A	
Ethyl cyanoacetate		A		
Ethyl ether (ether, diethyl ether)	A	A	A	
Ethyl formate			A	
Ethyl glycol (cellosolve)	A	A	A	
Ethyl lactate		A		
Ethyl mercaptan			A	
Ethyl methyl ketone	A	A	A	C
Ethyl oxalate		A	A	
Ethyl pentachlorobenzene		A	A	
Ethyl silicate		A	A	
Ethylbenzene	A	A	A	
Ethylcyclopentane			A	
Ethylene	A	A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Ethylene bromide		A	A	
Ethylene chloride (dichloroethane)	C	A	A	
Ethylene chlorohydrin (chloroethanol)	C	A	A	
Ethylene dibromide			A	
Ethylene dichloride (dichloroethylene, vinylidene chloride)		A	A	
Ethylene formate		A	A	
Ethylene glycol (glycol, 1,2-ethanediol)	A	A	A	A
Ethylene glycol monoethyl ether acetate		A		
Ethylene mercaptan		A	A	
Ethylene oxide	A	A	A	
Ethylene trichloride			A	
Ethylenediamine (1,2-diaminoethane)	A	A	A	
Ethylenediaminetetraacetic acid (EDTA)	A	A	A	
Ethylhexanol (isooctyl alcohol, 2-ethyl-1-hexanol)	A	A	A	C
FAM Test fuels DIN 51604 A			A	
FAM Test fuels DIN 51604 C			A	
Fats, cooking oils	A		A	
Fats, mineral	A	A	A	C
Fats, vegetable and animal	A	A	A	C
Fatty acids	A	A	A	C
Fatty alcohol sulfonates	A		A	
FC 43 Heptacosofluorotributylamine			A	A
FC 75			A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Ferric chloride (iron(III) chloride)	C	A	A	
Ferrous chloride (iron(II) chloride)	C	A	A	
Firewaters (ethyl alcohol, spirit)	A	A	A	C
Fixing baths	A		A	C
Fixing salt (antichlor, sodium thiosulfate)	C	A	A	A
Flaxseed oil (linseed oil)	A	A	A	A
Fluorammon (ammonium fluoride)	A	A	A	A
Fluoric acid (hydrofluoric acid), 4%		A	A	
Fluoric acid (hydrofluoric acid), 40%		A	A	
Fluoric acid (hydrofluoric acid), 50%		A	A	
Fluoric acid (hydrofluoric acid), 70%		A	A	
Fluoric acid (hydrofluoric acid), <65%, cold		A	A	
Fluoric acid (hydrofluoric acid), > 65%, cold			A	
Fluorides		A		
Fluorine		A	A	
Fluorine, dry		A	A	
Fluoroacetic acid			A	
Fluorobenzene			A	
Fluoroboric acid			A	
Fluorocarbons (FCs)			A	
Fluorochloroalkanes (CFCs)	A			
Fluorolub			A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Fluoronaphthalene (1-, 2-fluoronaphthalene)		A	A	
Fluoronitrobenzene (2-, 3-, 4-fluoronitrobenzene)		A	A	
Formaldehyde (formalin, methanal)	A	A	A	A
Formaldehyde (formalin, methanal), 10%	A	A	A	
Formaldehyde (formalin, methanal), 30%	A	A	A	
Formaldehyde (formalin, methanal), 40%	A	A	A	
Formamide	A	A	A	
Formic acid		A	A	C
Formic acid methyl ester (methyl formate)	A	A	A	C
Formic acid, 3%	A	A	A	
Formic acid, 50%		A	A	
Formic acid, 70%, +70 °C			A	
Formic acid, 98-100%		A	A	A
Freon (Frigen) 11	C	A	A	
Freon (Frigen) 112			A	
Freon (Frigen) 113	C	A	A	
Freon (Frigen) 114			A	
Freon (Frigen) 115			A	
Freon (Frigen) 12		A	A	
Freon (Frigen) 13 B1			A	
Freon (Frigen) 14			A	
Freon (Frigen) 218			A	
Freon (Frigen) 22		A	A	
Freon (Frigen) TA			A	A
Freon (Frigen) TC			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Freon (Frigen) TF			A	
Freon (Frigen) TMC			A	
Freon (Frigen) TP 35			A	A
Freon (Frigen) TWD 602			A	
Fructose	A	A	A	
Fruit juices	A	A	A	A
Fruit pulp	A	A	A	
Fruit wine	A	A		
Fryquel 90, 100, 150, 220, 300, 500			A	A
Fryquel A60			A	
Fuel + 20% ethanol	A		A	
Fuel + 20% methanol	A		A	
Fuel oil, black coal- and brown coal-based	A	A	A	
Fuel oil, mineral oil-based	A	A	A	
Fuel, premium	A		A	
Fuel, regular	A			
Fuel, unleaded			A	
Fumaric acid		A	A	C
Furan		A	A	
Furfural			A	
Furfuraldehyde			A	
Furfurol (furfuryl alcohol)	A	A	A	
Gallic acid (trihydroxyben- zoic acid)		A	A	A
Galvanic baths		A	A	C
Gas liquor		A	A	
Gas oil			A	
Gasoline	A	A	A	
Gasoline + 20% ethanol			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Gasoline + 20% methanol			A	
Gasoline, premium	A	A	A	
Gasoline, unleaded	A	A	A	
Gasoline/benzene 60/40 and 50/50		A	A	
Gasoline/benzene 80/20 and 70/30		A	A	
Gasoline/benzene/ethanol 50/30/20		A	A	
Gear oil Type A			A	C
Gear oil, mineral	A	A	A	C
Gelatine	A	A	A	
Gelatine, aqueous	A	A	A	A
Genantin (ethylene glycol)	A		A	
Generator gas			A	C
Girling brake fluid			A	
Glacial acetic acid (acetic acid), concentrated	C	A	A	C
Glauber's salt (sodium sul- fate)	A	A	A	A
Glucose (grape sugar)	A	A	A	A
Glue (animal glue)	A	A	A	A
Glycerine (glycerol)	C	A	A	A
Glycerol chlorohydrin			A	
Glycerol triacetate (tria- cetin)		A	A	A
Glyceryl nitrate (nitrogly- cerin)		A	A	
Glyceryl trinitrate (nitrogly- cerin)		A	A	
Glycol (ethylene glycol)	A	A	A	A
Glycolic acid (hydroxyacetic acid)		A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Glycolic acid (hydroxyacetic acid), 37%		A	A	
Glycolic acid (hydroxyacetic acid), 70%		A	A	A
Glysantin	A		A	
Grape sugar (glucose)	A	A	A	A
Green Liquor			A	
Gulf Endurance Oils			A	
Gulf FR Fluids Emulsion			A	
Gulf FR G-Fluids			A	A
Gulf FR P-Fluids			A	A
Gulf Harmony Oils			A	
Gulf High Temperature Grease			A	
Gulf Legion Oils			A	
Gulf Paramount Oils			A	
Gulf Security Oils			A	
Gulfcrown Grease			A	
Gum tragacanth	A	A	A	
Gypsum (calcium sulfate)	A	A	A	
Halon 1301			A	
Halothane			A	
Halowax oil			A	
Hannifin, Parker-O-Lube			A	C
HD Oil, motor oil free of aromatics	A		A	
Heavy water			A	A
HEF 2			A	
Helium gas	A	A	A	A
Henkel P3 solution			A	A
Heptane	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Hexachlorobenzene (HCB)	A			
Hexachlorobutadiene (tripen)	A		A	
Hexachlorocyclohexane			A	
Hexadecane			A	
Hexafluoroisopropylene		A	A	
Hexahydrobenzene (cyclo- hexane, hexamethylene)	A	A	A	C
Hexaldehyde	C	A	A	C
Hexalin (cyclohexanol)	A	A	A	
Hexamethylene (cyclo- hexane, hexahydrobenzene)	A	A	A	C
Hexanal (caprylaldehyde)			A	C
Hexane	A	A	A	C
Hexanetriol		A	A	A
Hexanoic acid			A	
Hexanol (hexyl alcohol)	A	A	A	C
Hexanol-1			A	
Hexene			A	
Hexyl alcohol (hexanol)	A	A	A	C
High Viscosity Lubricant H2			A	A
High Viscosity Lubricant U4			A	A
Honey	A	A	A	
Houghto Safe 1010 (phos- phate ester, HFD-R)			A	
Houghto Safe 1055 (phos- phate ester, HFD-R)			A	
Houghto Safe 1120 (phos- phate ester, HFD-R)			A	
Houghto Safe 271 (water/ glycol, HFC)			A	C
Houghto Safe 5040 (water/oil emulsion)			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Houghto Safe 620 (water/glycol, HFC)			A	C
Hydraulic fluid HFA, +50 °C				C
Hydraulic fluid HFB, +50 °C				C
Hydraulic fluid HFC, +60 °C				C
Hydraulic fluid HFD-R, +100 °C				A
Hydraulic fluid HFD-S, +100 °C				A
Hydraulic fluid H, HL, HLP (mineral oil-based)			A	
Hydraulic fluid HSA (oil-in-water emulsion)			A	
Hydraulic fluid HSB (water-in-oil emulsion)			A	
Hydraulic fluid HSC (polyglycol-based)			A	
Hydraulic fluid HSD a (R)			A	C
Hydraulic fluid HSD b (S)			A	C
Hydraulic fluid HSD c (T)			A	C
Hydraulic fluid, group H, HL, HLP (mineral oil-based)	A	A	A	
Hydraulic fluid, group HSA (oil-in-water emulsion)	A	A	A	
Hydraulic fluid, group HSB (water-in-oil emulsion)	A	A	A	
Hydraulic fluid, group HSC (polyglycol-based)	A	A	A	C
Hydraulic fluid, group HSD a (R) (phosphoric ester)	A	A	A	C
Hydraulic fluid, group HSD b (S) (phosphoric ester)	A	A	A	C
Hydraulic fluid, group HSD c (T) (phosphoric ester)	A	A	A	C
Hydraulic oils (mineral oil-based)	A		A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Hydrazine	A	A	A	
Hydrazine hydrate (diamide hydrate)	A	A	A	
Hydrazine, dry			A	
Hydro-Drive MIH 10, 50 (mineral oil-based)			A	C
Hydrobromic acid		A	A	
Hydrobromic acid, 40%		A	A	
Hydrobromic acid, 50%		A	A	
Hydrobromic acid, aqueous		A	A	
Hydrobromic acid, diluted		A	A	
Hydrochloric acid (muriatic acid), 1-5%		A	A	
Hydrochloric acid (muriatic acid), 10%		A	A	C
Hydrochloric acid (muriatic acid), 20%		A	A	
Hydrochloric acid (muriatic acid), 35%		A	A	
Hydrochloric acid (muriatic acid), 37%		A	A	
Hydrochloric acid (muriatic acid), 48%			A	
Hydrochloric acid (muriatic acid), concentrated		A	A	
Hydrochloric acid (spirits of salt)		A	A	
Hydrocyanic acid (hydrogen cyanide)	C	A	A	A
Hydrofluorosilicic acid (silicic acid)	A	A	A	
Hydrogen			A	
Hydrogen chloride		A	A	
Hydrogen peroxide, 10%		A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Hydrogen peroxide, 100%		A	A	
Hydrogen peroxide, 3%	A	A	A	
Hydrogen peroxide, 30%	A	A	A	A
Hydrogen peroxide, 8%		A	A	
Hydrogen peroxide, 90%	C	A	A	A
Hydrogen peroxide, diluted	A	A	A	A
Hydrogen phosphide		A	A	
Hydrogen sulfide	A	A	A	
Hydrogen sulfide, dry, cold			A	
Hydrogen sulfide, dry, hot			A	
Hydrogen sulfide, wet, cold			A	
Hydrogen sulfide, wet, hot			A	
Hydrogen sulfide, saturated	A			
Hydrogen, gaseous	A	A	A	
Hydroiodic acid		A	A	
Hydrolube (water/ethylene glycol)			A	C
Hydroquinone (1,4-dihydroxybenzene)		A	A	A
Hydroxyacetic acid (glycolic acid)		A	A	A
Hydroxylamine sulfate, aqueous		A	A	A
Hydyne			A	
Hypochlorous acid			A	
Industron FF44, FF48, FF53, FF80			A	
Ink	A	A	A	A
Iodine pentafluoride		A	A	
Iodine tincture	A	A	A	C
Iodine, dry		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Iodine-potassium iodide solution	C	A	A	
Iodoform (triiodomethane)		A	A	
Iron chloride, aqueous		A	A	A
Iron nitrate, aqueous	A	A	A	C
Iron nitrate, saturated		A	A	
Iron sulfate (iron vitriol), aqueous	A	A	A	C
Iron(II) chloride, aqueous (ferrous chloride)	C	A	A	
Iron(II) sulfate		A	A	
Iron(II) sulfate, aqueous		A	A	
Iron(II) sulfate, saturated		A	A	
Iron(III) chloride (ferric chloride)	C	A	A	
Iron(III) sulfate		A	A	
Isoamyl alcohol	A	A	A	C
Isobutanol (isobutyl alcohol)	A	A	A	A
Isobutyl acetate	A	A	A	
Isobutyl alcohol (isobutanol)	A	A	A	A
Isobutyl butyrate			A	
Isobutyl methyl ketone		A	A	
Isobutyraldehyde				C
Isododecane			A	
Isooctane	A	A	A	
Isooctyl alcohol (ethylhexanol)	A	A	A	C
Isophorone			A	
Isopropanol (2-propanol)	A	A	A	A
Isopropyl acetate	A	A	A	
Isopropyl alcohol (isopropanol, persprit)	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Isopropyl chloride		A	A	
Isopropyl ether (diisopropyl ether)		A	A	
Isopropyl formate			A	C
Isopropylacetone (methyl isobutyl ketone, MIBK)	A	A	A	
Isopropylbenzene (cumene)	A	A	A	
Jam		A	A	
Javel water (sodium hypochlorite, bleaching solution)		A	A	C
JP 3 (MIL-J-5624)			A	
JP 4 (MIL-J-5624)			A	
JP 5 (MIL-J-5624)			A	
JP 6 (MIL-J-5624)			A	
JP X (MIL-F-25604)			A	
KEL-F liquid			A	A
Kerosene	A	A	A	
Keystone # 87HX-Grease			A	
Lactam			A	
Lactic acid	A	A	A	C
Lactic acid, 3%	A	A	A	
Lactic acid, 80%	C	A	A	
Lactic acid, aqueous	C	A	A	A
Lactic acid, concentrated	C	A	A	
Lactose	A	A	A	A
Lanolin (wool grease)	A	A	A	C
Lard		A	A	C
Lard, animal fat			A	C
Latex	A		A	
Laughing gas (nitrous oxide)	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Lauric acid (dodecanoic acid)		A	A	
Lauryl alcohol (dodecanol)		A	A	
Lauryl chloride		A	A	
Lavender oil	A	A	A	
Lead acetate (lead sugar)	A	A	A	
Lead nitrate		A	A	C
Lead stearate		A	A	
Lead sugar (lead acetate)	A	A	A	
Lead sulfamate			A	
Lead sulfate		A	A	C
Lead tetraethyl (tetraethyl lead, TEL)		A	A	
Lead(II) acetate	A	A	A	
Lead(II) acetate, aqueous	A	A	A	
Lead(II) nitrate		A	A	
Lead(II) nitrate, aqueous		A	A	
Lehigh X1 169			A	
Lehigh X1 170			A	
Lemon juice	A	A	A	
Lemon peel oil		A		
Light oil (crude benzene)			A	
Ligroin (white spirit)			A	
Lindol, hydraulic fluid (phosphate ester)			A	
Linoleic acid		A	A	C
Linseed oil (flaxseed oil)	A	A	A	A
Liqueurs	A	A	A	A
Liqui Moly			A	
Liquid manure	A	A	A	A
Liquid soaps	A	A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Lithium bromide			A	
Lithium bromide, aqueous	A	A	A	A
Lithium chloride, aqueous	A	A	A	A
Lubricating oil (diester-based)			A	
Lubricating oil (mineral oil-based)	A	A	A	C
Lubricating oil (SAE 10, 20, 30, 40, 50)			A	
Lyes, diluted	A	A	A	C
Lysol		A	A	A
Machine oil	A		A	
Magnesium bromide	A	A	A	
Magnesium carbonate	A	A	A	A
Magnesium chloride, aqueous	A	A	A	A
Magnesium chlorite	A		A	A
Magnesium hydroxide	A	A	A	A
Magnesium iodide	A	A	A	
Magnesium nitrate	A	A	A	
Magnesium sulfate (Epsom salt)	A	A	A	A
Magnesium sulfide			A	A
Magnesium sulfite			A	A
Malathion			A	
Maleic acid (cis-butenedioic acid), aqueous		A	A	
Maleic acid (cis-butenedioic acid), saturated		A	A	
Maleic anhydride			A	
Malic acid			A	
Margarine	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
MCS 312			A	A
MEK (butanone, methyl ethyl ketone)	A	A	A	C
Menthol		A	A	
Mercury	A	A	A	A
Mercury (II) chloride	C	A	A	
Mercury (II) cyanide		A	A	
Mercury chloride	C	A	A	
Mercury chloride, aqueous	A	A	A	A
Mercury nitrate		A	A	A
Mersol D			A	
Mesityl oxide (diacetone alcohol)			A	
Methacrylic acid			A	
Methanal (formaldehyde)	A	A	A	A
Methane	A	A	A	
Methane (mine gas, natural gas)	A	A	A	C
Methanol (methyl alcohol, wood alcohol)	A	A	A	A
Methoxybenzene (anisole, methyl phenyl ether)	C	A	A	
Methoxybutanol (methoxybutyl alcohol)		A	A	
Methoxybutyl alcohol (methoxybutanol)		A	A	
Methoxyethyl oleate		A		
Methyl acetate (acetic acid methyl ester)	C	A	A	
Methyl acetoacetate				C
Methyl alcohol (methanol, wood alcohol)	A	A	A	A
Methyl bromide		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Methyl butanol	A		A	
Methyl butyl ether	C	A	A	
Methyl butyl ketone		A	A	C
Methyl carbonate			A	
Methyl cellosolve (methyl glycol acetate)	C	A	A	C
Methyl cellulose			A	C
Methyl chloride		A	A	
Methyl chloroform (trichloroethane, chloroethene)	C	A	A	
Methyl cyanide (acetonitrile)		A	A	
Methyl dichloroacetate		A	A	
Methyl ethyl ether			A	
Methyl ethyl ketone peroxide				C
Methyl formate (formic acid methyl ester)	A	A	A	C
Methyl glycol	A	A	A	
Methyl glycol acetate (methyl cellosolve)	C	A	A	C
Methyl isobutyl ketone (isopropylacetone, MIBK)	A	A	A	
Methyl methacrylate			A	C
Methyl monochloroacetate			A	
Methyl phenyl ether (anisole, methoxybenzene)			A	
Methyl salicylate			A	
Methylamine (monomethylamine)	A	A	A	
Methylaniline			A	
Methylbenzene (toluene)	A	A	A	C
Methylcatechol (creosol)			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Methylcyclohexane			A	
Methyl methacrylate		A		
Methyl monochloroacetate		A		
Methyl phenyl ether (anisole, methoxybenzene)	C	A		
Methylene chloride (dichloromethane)	C	A	A	C
Methylene chlorobromide (chlorobromomethane)	C	A	A	
Methylpentane (2-)			A	
Methylsulfuric acid, 50%			A	
Milk	A	A	A	A
Milk of lime (calcium hydroxide)	A	A	A	A
Mine gas (methane, natural gas)	A	A	A	C
Mineral oils	A	A	A	C
Mineral water	A	A	A	A
Molasses	A	A	A	A
Molasses wort		A	A	
Monobromobenzene	A	A	A	
Monochloroacetic acid		A	A	
Monochloroacetic acid ester	A	A	A	
Monochlorobenzene (chlorobenzene)	A	A	A	A
Monochloroethyl acetate			A	
Monoethanolamine		A	A	C
Mononitrotoluene			A	
Monovinylacetylene				C
Morpholine (diethylene oxide)		A	A	
Mowilith D			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Mustard	A	A		
Mustard gas				A
Myristyl alcohol (myristic alcohol)	A	A	A	
n-amyl acetate	A	A	A	
n-pentane		A	A	
Naftolen ZD			A	
Naphtha	A	A	A	C
Naphthalene (in alcohol)	A		A	
Naphthalene (rock oil)	A	A	A	
Naphthenic acid			A	
Natural gas (mine gas, methane)	A	A	A	C
Neatsfoot oil		A	A	C
Nekal BX, aqueous			A	
Neon gas	A	A	A	A
Nevile and Winther's acid			A	
Nickel acetate, aqueous		A	A	
Nickel chloride		A	A	A
Nickel nitrate	A	A	A	A
Nickel sulfate	A	A	A	A
Nickel sulfate, aqueous	A	A	A	
Nickel sulfate, saturated	A	A	A	
Nickel(II) chloride	A	A	A	
Nicotine, aqueous	A	A	A	
Nicotinic acid	A	A	A	
Nitric acid, 1-10%		A	A	C
Nitric acid, 10%		A	A	C
Nitric acid, 100%			A	
Nitric acid, 3-molar			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Nitric acid, 30%		A	A	
Nitric acid, 50%		A	A	
Nitric acid, 65% (aqua fortis)		A	A	
Nitric acid, 66%		A	A	
Nitric acid, 70%		A	A	
Nitric acid, fuming		A	A	
Nitroalcohol (nonanol)		A	A	
Nitrobenzene (oil of mirbane)	C	A	A	
Nitrobutanol		A	A	
Nitroethane			A	
Nitrogen	A	A	A	A
Nitrogen tetroxide			A	
Nitroglycerin (glyceryl nitrate)		A	A	
Nitroglycerin (glyceryl trinitrate)		A	A	
Nitroglycol, aqueous		A	A	
Nitromethane		A	A	
Nitropropane			A	
Nitrosulfuric acid		A	A	
Nitrotoluene	C	A	A	
Nitrous acid		A	A	
Nitrous fumes			A	
Nut oil			A	A
O-A-548A				C
Octachlorotoluene			A	
Octadecane		A	A	
Octafluorocyclobutane	A			
Octal (dioctyl phthalate, DOP)	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Octane	A	A	A	
Octane chlorotoluene			A	
Octanol			A	
Octyl alcohol	A	A	A	C
Octyl cresol		A	A	
Oil of mirbane (nitrobenzene)	C	A	A	
Oils and fats, vegetable			A	
Oils, essential			A	
Oleic acid	A	A	A	
Oleum (fuming sulfuric acid)		A	A	
Oleyl alcohol			A	
Olive oil	A	A	A	C
Orange juice		A	A	
Orange peel oil	A		A	
Oronite 8200, 8515			A	
Ortho-chloroethyl benzene			A	
OS 45 type III (OS45)			A	
OS 45 type IV (OS45-1)			A	
OS 70			A	
Oxalic acid (ethanedioic acid)	A	A	A	A
Oxalic acid (ethanedioic acid), aqueous		A	A	C
Oxygen	A	A	A	A
Oxygen, gaseous, cold			A	A
Ozone			A	C
Ozone air mixture		A	A	A
P3 solution			A	A
P3 solution, aqueous	A			
Paint thinners		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Palatinol A (dibutyl phthalate)	A	A	A	C
Palm kernel fatty acid			A	
Palm kernel oil			A	
Palm oil			A	
Palmitic acid	C	A	A	
Para-dichlorobenzene			A	
Paraffin (alkane)	A	A	A	
Paraffin emulsion			A	
Paraffin oil	A	A	A	A
Paraffin wax, molten	A	A	A	A
Parker-O-Lube				C
Peanut oil	A	A	A	A
Pectin	A	A	A	A
Pectin, aqueous	A	A	A	A
Penicillin		A		
Pentachlorodiphenyl			A	
Pentane	A			
Pentane, 2,4-dimethyl			A	
Pentane, 2-methyl			A	
Pentane, 3-methyl			A	
Pentane, n-			A	
Pentanol (pentyl alcohol, amyl alcohol)	A	A	A	
Pentyl alcohol (pentanol, amyl alcohol)	A	A	A	
Pentyl chloride (amyl chloride, 1-chloropentane)	A	A	A	
Peracetic acid		A	A	
Perchloric acid	C	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Perchloric acid (hyperchloric acid)	C	A	A	C
Perchloric acid 2N			A	
Perchloric acid, 20%		A	A	
Perchloric acid, 70%		A	A	
Perchloroethylene (tetrachloroethylene)	C	A	A	
Perfume		A	A	
Perfluoropropane	A			
Petroleum	A	A	A	C
Petroleum ether	A	A	A	C
Phenol (carbolic acid)		A	A	
Phenol (carbolic acid), 70%, water, 30%			A	
Phenol (carbolic acid), 85%, water 15%			A	
Phenyl ethyl ether			A	
Phenylbenzene			A	
Phenylcarbinol (benzyl alcohol)	A	A	A	C
Phenylethanol		A	A	
Phenylethyl alcohol (benzyl carbinol)	A	A	A	
Phenylhydrazine	A	A	A	
Phenylhydrazine HCl			A	
Phorone			A	
Phosgene, gaseous			A	
Phosgene, liquid	C	A	A	
Phosphates		A	A	
Phosphine	A		A	
Phosphoric acid, 1-5%	C	A	A	
Phosphoric acid, 10%	C			

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Phosphoric acid, 20%		A	A	C
Phosphoric acid, 30%		A	A	A
Phosphoric acid, 45%			A	
Phosphoric acid, 50%			A	A
Phosphoric acid, 85%	A	A	A	C
Phosphoric acid, concentrated		A	A	
Phosphorus oxychloride		A	A	
Phosphorus pentachloride			A	
Phosphorus pentoxide			A	
Phosphorus pentoxide		A	A	
Phosphorus trichloride	C	A	A	
Photo developers	A	A	A	A
Photographic developers	A		A	
Photographic emulsions	A		A	
Phthalic acid (benzene-o-dicarboxylic acid)	A	A	A	A
Phthalic anhydride, aqueous			A	A
Picric acid, aqueous	C	A	A	
Picric acid, molten			A	
Pine needle oil			A	C
Pine oil		A	A	
Pine oil, +70 °C			A	
Pine tar (creosote)		A	A	
Pineapple juice		A	A	
Pinene			A	
Piperidine		A	A	
Polyethylene glycol	A			
Polyglycol		A	A	
Polysolvan O	A			

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Polyvinyl acetate emulsion			A	
Potassium acetate	A	A	A	
Potassium bichromate		A	A	
Potassium bichromate, 10%	A			
Potassium bisulfate		A	A	C
Potassium borate		A	A	C
Potassium borate, 10%	A	A	A	
Potassium bromate		A	A	C
Potassium bromate, aqueous			A	
Potassium bromate, saturated			A	
Potassium bromide	A	A	A	
Potassium carbonate	A	A	A	A
Potassium carbonate (potash)	A	A	A	A
Potassium carbonate (potash), aqueous	A	A	A	C
Potassium carbonate, aqueous	A	A	A	C
Potassium chlorate		A	A	
Potassium chlorate, aqueous	A		A	
Potassium chlorate, saturated	A		A	
Potassium chloride (sylvine)	A	A	A	A
Potassium chromate, yellow		A	A	
Potassium chromate, yellow, aqueous			A	
Potassium chromate, yellow, saturated			A	
Potassium copper cyanide			A	A
Potassium cyanide	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Potassium cyanide, aqueous	C	A	A	
Potassium cyanide, saturated	C	A	A	
Potassium dichromate		A	A	
Potassium dichromate, aqueous	C		A	A
Potassium dichromate, saturated	C		A	
Potassium ferricyanide	A	A	A	
Potassium ferrocyanide	A	A	A	
Potassium fluoride	A	A	A	
Potassium hydrogen carbonate	A	A	A	
Potassium hydrogen sulfate	A	A	A	
Potassium hydrogen sulfate, aqueous	A	A	A	
Potassium hydrogen tartrate		A	A	
Potassium hydroxide (caustic potash, potash lye)	A	A	A	A
Potassium hydroxide (caustic potash, potash lye), 1%	A	A	A	
Potassium hydroxide (caustic potash, potash lye), 10%	A	A	A	
Potassium hydroxide (caustic potash, potash lye), 30%			A	
Potassium hydroxide (caustic potash, potash lye), 50%	C	A	A	
Potassium hypochlorite		A	A	
Potassium iodate			A	
Potassium iodide		A	A	A
Potassium iodide, aqueous	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Potassium iodide, saturated	A	A	A	
Potassium nitrate (salt-peter)	A	A	A	A
Potassium nitrate (salt-peter), 50%	A	A	A	
Potassium nitrate (salt-peter), aqueous	A	A	A	
Potassium perchlorate		A	A	
Potassium perchlorate, aqueous	A	A	A	
Potassium perchlorate, saturated	A	A	A	
Potassium permanganate	C	A	A	
Potassium permanganate, 1%	A			
Potassium permanganate, aqueous	C	A	A	
Potassium persulfate	C	A	A	
Potassium sulfate	C	A	A	A
Potassium sulfide			A	
Potassium sulfite	A	A	A	A
Potassium thiosulfate	A	A	A	
Prestone antifreeze			A	A
PRL high temperature hydraulic oil			A	C
Propanal (propionaldehyde)		A	A	
Propane, gaseous	A	A	A	
Propane, liquid	A	A	A	
Propanecarboxylic acid (butyric acid, butanoic acid)	C	A	A	
Propanediol (propylene glycol)	A	A	A	
Propanol (propyl alcohol)	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Propanone (acetone, dimethyl ketone)	C	A	A	A
Propargyl alcohol			A	
Propargyl alcohol, aqueous			A	
Propene	A		A	
Propionic acid (methyl acetic acid)		A	A	
Propionic acid (methyl acetic acid), 50%			A	
Propyl acetate	A	A	A	
Propyl acetone, n-			A	
Propyl alcohol (propanol)	A	A	A	C
Propyl nitrate		A	A	
Propylamine	C	A	A	
Propylene	A	A	A	
Propylene glycol (propane-diol)	A	A	A	
Propylene oxide		A	A	
Prussic acid (hydrocyanic acid)	C	A	A	A
Pseudocumene			A	
Pyanol		A	A	C
Pydraul C				C
Pydraul E (29, 30, 50, 65, 90, 11)				C
Pydraul 30E, 50E, 65E, 90E (HFD-R)				A
Pydraul F9				A
Pyranol, transformer oil (PCB)			A	
Pyranton (diacetone alcohol, Dial, DA)	A	A	A	A
Pyridine	C	A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Pyrogallol (pyrogalllic acid)	C	A	A	
Pyrogard 42, 43, 53, 55 (HFD-R)			A	
Pyrogard C, D			A	C
Pyrolube			A	C
Pyrrole		A	A	C
Quinine		A	A	
Rapeseed oil		A	A	A
RED Oil (MIL-H-5606)			A	
Refrigerant R TA				A
Refrigerant R TP 35				A
Resorcinol (1,3-dihydroxy- benzene)		A	A	
Resorcinol, 5%		A		
RJ-I (MIL-F-25558)			A	
RJ-I (MIL-F-25576)			A	
Rubber dispersion	A			
Saccharic acid		A	A	
Sal ammoniac (ammonium chloride)	C	A	A	A
Sal volatile (ammonium car- bonate)	A	A	A	
Salicylaldehyde		A	A	
Salicylic acid (o-Hydroxy- benzoic acid)		A	A	A
Salicylic acid, powder		A	A	
Salicylic acid, saturated		A	A	
Salt water (sea water)	A	A	A	A
Saltpeter (potassium nitrate)	A	A	A	A
Santo Safe 300			A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Saturated steam condensate			A	
Sea water (salt water)	A	A	A	A
Selenium chloride		A	A	
Silicate ester			A	
Silicic acid (hydrofluorosilicic acid)	A	A	A	
Silicone grease	A	A	A	
Silicone oil	A	A	A	
Silver acetate	C	A	A	A
Silver cyanide		A		
Silver nitrate (lunar caustic)	C	A	A	A
Silver nitrate (lunar caustic), aqueous	A	A	A	
Sinclair Opaline CX-EP Lube			A	
Skelly, Solvent B, C, E			A	
Skydrol 500 (B4)		A		
Soap water (soap hydrous solution)	A	A	A	A
Socony Mobile Type A			A	
Socony Vacuum AMV AC 781			A	
Socony Vacuum PD959B			A	
Soda (sodium carbonate)	A	A	A	A
Soda (sodium carbonate), aqueous	A	A	A	A
Sodium acetate	A	A	A	A
Sodium aluminum sulfate		A	A	
Sodium benzoate	A	A	A	
Sodium benzoate, aqueous	A	A	A	A
Sodium bicarbonate, aqueous	A	A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Sodium bisulfate	A	A	A	A
Sodium bisulfate, aqueous	A	A	A	A
Sodium bisulfite, aqueous		A	A	A
Sodium borate, aqueous	A	A	A	A
Sodium borate, saturated	A	A	A	
Sodium bromate	A		A	
Sodium bromide	A	A	A	
Sodium carbonate (soda)	A	A	A	A
Sodium carbonate (soda), aqueous	A	A	A	A
Sodium chlorate	A	A	A	
Sodium chlorate, aqueous	A	A	A	A
Sodium chloride (common salt)	A	A	A	A
Sodium chlorite, aqueous		A	A	
Sodium chlorite, diluted			A	
Sodium chromate			A	
Sodium cyanide	A	A	A	A
Sodium cyanide, aqueous	C	A	A	
Sodium cyanide, saturated	C	A	A	
Sodium dichromate	A	A	A	C
Sodium dichromate, aqueous		A	A	
Sodium dithionite			A	
Sodium dodecylbenzenesul- fonate	A		A	
Sodium fluoride	A	A	A	C
Sodium hexacyanoferrate(II)		A	A	
Sodium hexametaphos- phate	A	A	A	
Sodium hydroxide (caustic soda, soda lye)	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Sodium hydroxide (caustic soda, soda lye), 1%	A	A	A	
Sodium hydroxide (caustic soda, soda lye), 30%	A	A	A	
Sodium hydroxide (caustic soda, soda lye), 45%	A		A	
Sodium hydroxide (caustic soda, soda lye), 50%	A	A	A	C
Sodium hydroxide (caustic soda, soda lye), 60%			A	
Sodium hydroxide (caustic soda, soda lye), concentrated			A	
Sodium hypochlorite (bleaching solution, Javel water)		A	A	C
Sodium hypochlorite (bleaching solution, Javel water), 12.5%		A	A	C
Sodium hypochlorite (bleaching solution, Javel water), 15%		A	A	C
Sodium hypochlorite (bleaching solution, Javel water), diluted		A	A	C
Sodium hypochlorite (bleaching solution, Javel water), saturated		A	A	C
Sodium iodide	A	A	A	
Sodium metabisulfite			A	
Sodium metaphosphate		A	A	
Sodium metasilicate			A	
Sodium nitrate (Chile salt-peter)	A	A	A	C
Sodium nitrate (Chile salt-peter), aqueous	A	A	A	
Sodium nitrate (Chile salt-peter), saturated	A	A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Sodium nitrite		A	A	
Sodium nitrite, aqueous	A		A	
Sodium nitrite, saturated	A		A	
Sodium oxalate	A	A	A	
Sodium perborate	A	A	A	C
Sodium perborate, aqueous	A		A	
Sodium perborate, saturated	A		A	
Sodium perchlorate	A		A	A
Sodium peroxide		A	A	
Sodium peroxide, saturated			A	
Sodium persulfate			A	
Sodium phosphate	A	A	A	
Sodium phosphate, aqueous	A	A	A	
Sodium phosphate, saturated	A	A	A	
Sodium silicate		A	A	
Sodium silicate, aqueous	A	A	A	
Sodium stearate	A	A	A	A
Sodium sulfate (Glauber's salt)	A	A	A	A
Sodium sulfate (Glauber's salt), aqueous	A	A	A	
Sodium sulfate (Glauber's salt), saturated	A	A	A	
Sodium sulfide	A	A	A	A
Sodium sulfide, aqueous	A	A	A	
Sodium sulfide, saturated	A	A	A	
Sodium sulfite	A	A	A	A
Sodium tetraborate (borax)	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Sodium thiosulfate (anti-chlor, fixing salt)	C	A	A	A
Soft soap	A	A	A	
Sovasol 1, 2, 3			A	
Sovasol 73, 74			A	
Soybean oil	A	A	A	A
Spent sulfite liquors			A	
Spermaceti	A	A	A	
Spin bath acids			A	
Spindle oil (mineral oil-based)			A	
Spirit (ethyl alcohol, ethanol)	A	A	A	C
Spruce oil (spruce needle oil)	A	A	A	
Spry			A	A
SR-10 Fuel			A	
SR-6 Fuel			A	
Standard Oil Mobilube GX90-EP Lube			A	
Starch	A	A	A	
Starch sirup	A	A	A	
Starch, aqueous	A	A	A	A
Stauffer 7700			A	
Stauffer grease			A	
Stearic acid (zinc salt)	A	A	A	A
Stearyl alcohol (1-octadecanol)		A	A	
Strontium bromide		A	A	
Strychnine		A	A	
Styrene (styrol)	A	A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Styrene (vinyl benzene, phenylethene)	A	A	A	C
Succinic acid	C	A	A	
Succinic acid, 50%		A	A	
Succinic acid, saturated		A	A	
Suds	A	A	A	A
Sugar beet juice	A	A	A	A
Sugar cane solution			A	A
Sugar sirup	A	A	A	A
Sulfur	A	A	A	
Sulfur chloride (disulfur dichloride)		A	A	
Sulfur dichloride		A	A	
Sulfur dioxide		A	A	C
Sulfur dioxide, dry			A	C
Sulfur dioxide, liquid		A	A	C
Sulfur dioxide, wet		A	A	C
Sulfur hexafluoride	A		A	A
Sulfur trioxide		A	A	C
Sulfur, liquid, +60 °C			A	C
Sulfuric acid monohydrate, 97.9-99%		A	A	
Sulfuric acid, 1-6%		A	A	
Sulfuric acid, 10%		A	A	A
Sulfuric acid, 20%		A	A	
Sulfuric acid, 25%			A	
Sulfuric acid, 3-molar			A	
Sulfuric acid, 40%		A	A	
Sulfuric acid, 50%			A	
Sulfuric acid, 60%		A	A	
Sulfuric acid, 80%		A	A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Sulfuric acid, 95%		A	A	
Sulfuric acid, fuming			A	
Sulfuric acid, fuming (20/25% oleum)		A	A	
Sulfurous acid		A	A	C
Sulfuryl chloride		A	A	
Sunoco # 3661			A	
Sunoco SAE 10			A	
SunSAFE (fire-resistant hydraulic fluid)			A	
Surfactant			A	
Swan Finch EP Lube			A	
Swan Hypoid-90			A	
Tallow	A	A	A	
Tanigan extra A, aqueous, +20 °C			A	
Tanigan extra B, aqueous, +20 °C			A	
Tanigan extra C, aqueous, +100 °C			A	
Tanigan extra D, aqueous, +20 °C			A	
Tanigan extra F, aqueous, +20 °C			A	
Tanigan extra U, aqueous, +20 °C			A	
Tannic acid (tannin)	C	A	A	C
Tannin (tannic acid)	C	A	A	C
Tanning extracts, vegetable			A	
Tar	A	A	A	C
Tartaric acid (dihydroxysuc- cinic acid)	C	A	A	A
Terpineol			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Test fuel A (ISO-Fluid A)			A	
Test fuel B (ISO-Fluid B)			A	
Test fuel C (ISO-Fluid C)			A	
Test fuel D (ISO-Fluid D)			A	
Tetrabromoethane (acetylene tetrabromide, TBE)		A	A	
Tetrabromomethane			A	
Tetrabutyltitanate			A	
Tetrachloride			A	
Tetrachloroethane (acetylene tetrachloride)	A	A	A	
Tetrachloroethylene (perchloroethylene)	C	A	A	
Tetrachloromethane (carbon tetrachloride)	C	A	A	
Tetraethyl lead (lead tetraethyl, TEL)		A	A	
Tetrafluoromethane	A			
Tetrahydrofuran (diethylene oxide, tetramethylene oxide)	C	C	A	C
Tetrahydronaphthalene (tetralin)	A	A	A	
Tetralin (tetrahydronaphthalene)	A	A	A	
Tetramethylammonium hydroxide (tetramine)		A	A	
Tetramethylene chloride (dichlorobutane)			A	
Tetramethylene oxide (tetrahydrofuran)	C	C	A	C
Thiofuran (thiol, thiophene)	C	A	A	
Thioglycolic acid			A	
Thiokol TP 90B (polyester plasticizer)			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Thiokol TP 95			A	
Thionyl chloride	A	A	A	
Thiophene (thiofuran, thiol)	C	A	A	
Tidewater Multigear 140, EP Lube			A	
Tidewater Oil-Beedol			A	C
Tin (II) chloride		A	A	
Tin (IV) chloride		A	A	
Tin chloride, 50%			A	C
Tin chloride, aqueous		A	A	
Titanium tetrachloride		A	A	
Toluene (methylbenzene)	A	A	A	C
Toluene diisocyanate			A	
Train oil				A
Transformer oil	A			
Transformer oil (mineral oil-based)	C	A	A	C
Transmission Fluid Type A			A	C
Triacetin (glycerol triacetate)		A	A	A
Triaryl phosphate			A	
Tributoxyethylphosphate			A	
Tributyl citrate		A		
Tributyl mercaptan		A	A	
Tributyl phosphate (triethyl phosphate)		A	A	
Trichloroacetic acid		A	A	
Trichlorobenzene (trichlorophenol)		A	A	
Trichloroethane (chloroethene, methyl chloroform)	C	A	A	
Trichloroethylene		A	A	C

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Trichlorofluoromethane	A			
Trichloromethane (chloroform)		A	A	C
Trichlorophenol (trichlorobenzene)		A	A	
Trichlorotrifluoroethane	A	A	A	
Tricresyl phosphate	A		A	A
Triethanolamine (triethylolamide)	A	A	A	
Triethyl phosphate (tributyl phosphate)		A	A	
Triethylamine (TEA)	A	A	A	
Triethylene glycol	A	A	A	A
Trifluoroacetic acid (TFA)		A	A	
Trifluoroethane		A	A	
Trifluorotrichloroethane	A			
Triglycol	A	A		
Triglycol acetate	A			
Triisopropylbenzene			A	
Trilone B, 10%	A			
Trimethylolpropane	A	A	A	
Trioctylphosphate		A	A	
Tripin (hexachlorobutadiene)	A		A	
Tripolyphosphate			A	
Tripropylene glycol (TPG)	A	A	A	A
Trisodium phosphate	A	A	A	A
Tung oil (China wood oil)			A	
Turbine oil No. 35 (MIL-L-7808A)			A	
Turbine oil, mineral	A	A	A	C
Turbo oil No. 35			A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Turpentine	A	A	A	C
Two-stroke (engine) oil	A		A	
Undecyl alcohol	A	A	A	
Univis 40 (hydraulic fluid)			A	
Univolt 35 (mineral oil)			A	
Urea	A	A	A	A
Urea, aqueous	A	A	A	A
Uric acid	A	A	A	
Urine	A	A	A	A
Valerian drops		A	A	
Varnish		A	A	
Vaseline	A		A	A
Vaseline oil	A	A	A	C
Vegetable oil	A	A	A	A
Versilube F-50			A	
Vinegar	A	A	A	A
Vinyl acetate (acetic acid ethenyl ester)		A	A	
Vinyl acetylene			A	C
Vinyl chloride (monochloro- ethylene)		A	A	
Vinylidene chloride (dichloroethylene, ethylene dichloride)		A	A	
Viscose spinning solution			A	
Vitamin C		A	A	
Walnut oil			A	
Washing agents			A	
Waste gases, alkaline			A	
Waste gases, containing carbon dioxide		A	A	A

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Waste gases, containing carbon monoxide		A	A	A
Waste gases, containing hydrochloric acid		A	A	
Waste gases, containing hydrogen fluoride		A	A	
Waste gases, containing nitrous gas (nitrogen oxides)		A	A	
Waste gases, containing sulfur dioxide		A	A	
Waste gases, containing sulfur trioxide			A	
Waste gases, containing sulfuric acid		A	A	
Wastewater			A	A
Water glass (potassium silicate)		A	A	A
Water glass (sodium silicate)		A	A	A
Water vapour, +120 °C		A	A	C
Water, distilled	A	A	A	
Water, with carbon dioxide	A	A	A	
Water/Spring water, cold	A	A	A	A
Wax alcohols		A	A	
Waxes			A	
Wax molten	A			
Wemco C			A	
Whey		A	A	
Whisky	A	A	A	A
White liquor		A	A	
White oil		A	A	
White pine oil			A	
White spirit	A		A	

List of chemical resistance

Fluid Source: Reichelt Chemietechnik https://www.rct-online.de	POM	FEP	PTFE	Silicone
Wine, brandy	A	A	A	A
Wolman salt (wood preservative)			A	A
Wood alcohol (methanol, methyl alcohol)	A	A	A	A
Wood oil	A	A	A	
Wool grease (lanolin)	A	A	A	C
Xenon	A	A	A	A
Xylamon		A	A	C
Xylene (dimethylbenzene)	A	A	A	C
Xylidene		A	A	
Yeast	A	A	A	
Yeast, aqueous			A	A
Zeolites		A	A	
Zinc acetate, aqueous		A	A	
Zinc bromide		A	A	
Zinc carbonate	A	A	A	A
Zinc chloride	A	A	A	A
Zinc chloride, 10%	A	A	A	
Zinc chloride, aqueous	C	A	A	
Zinc nitrate		A	A	
Zinc ointment			A	
Zinc oxide	A	A	A	A
Zinc phosphate	A	A	A	A
Zinc salt (stearic acid)	A	A	A	A
Zinc stearate	A	A	A	
Zinc sulfate	A	A	A	A
Zinc sulfate, 10%	A	A	A	
Zinc sulfate, aqueous		A	A	A

List of chemical resistance

The CHEMICAL PROPERTIES of N-BK7 glass see: https://www.schott.com/d/advanced_optics/c36214d9-13c4-468c-bf40-8d438b89f532/1.30/schott-optical-glass-pocket-catalog-jan-2020-row.pdf



© 2020

Fritsch GmbH
Milling and Sizing
Industriestrasse 8
D - 55743 Idar-Oberstein
Telephone: +49 (0) 6784/ 70-0
Email: info@fritsch.de
Internet: www.fritsch.de
